



## CHEMISTRY

### BOOKS - CENGAGE CHEMISTRY (HINGLISH)

#### SOLID STATE

#### Illustration

1. A sample of a crystalline solid scatters a beam of X-rays of wavelength  $70.93 \text{ pm}$  at an angle  $2\theta$  of  $14.66^\circ$ . If this is a second-order reflection ( $n = 2$ ), calculate the distance between the parallel planers

of atoms from which the scattered beam appears to have been reflected.



[Watch Video Solution](#)

2. Calculate  $\lambda$  of X-rays which give a diffraction angle  $2\theta = 16.8^\circ$  for crystal, if the interplanar distance in the crystal is  $0.2nm$  and that only for the first-order diffraction is observed. Given  $\sin 8.40^\circ = 0.146$ .



[Watch Video Solution](#)

3. A compound formed by elements  $X$  and  $Y$  has a cubic structure in which  $X$  atoms are at the face centres.

a. Calculate: (i)  $Z_{eff}$ , (ii) total number of atoms in a cube, and (iii) formula of the compound.

b. If all the atoms are removed from a single axis passing through the centre of the cube, calculate

(i)  $Z_{eff}$ , (ii) total number of atoms in a cube, and (iii) formula of the compound.



[Watch Video Solution](#)

4. A compound formed by elements  $X$  and  $Y$  has a cubic structure in which  $X$  atoms are at the corners of the cube and two atoms ( $Y$ ) are at each body diagonal of the cube.

a. Calculate: (i)  $Z_{eff}$ , (ii) total number of atoms in a cube, and (iii) formula of the compound.

b. If all atoms form one body diagonal of the cube except corners are removed, calculate: (i)  $Z_{eff}$ , (ii) total number of atoms in the cube, and (iii) formula of the compound.



[Watch Video Solution](#)

5. A compound formed by elements  $X$  and  $Y$  has a cubic structure in which  $X$  atoms are at the corner of the cube and  $Y$  atoms are at the face centres.

One atoms  $X$  is missing from the corner.

a. Calculate (i).  $Z_{eff}$ , (ii). total number of the atoms in the cube, and (iii). formula of the compound.

b. If all the atoms are removed from one of the faces of the cube containing atoms at corners, as in

(a) above, calculate (i)  $Z_{eff}$ , (ii) total number of atoms in a cube, and (iii) formula of the compound.



**Watch Video Solution**

6. A compound formed by elements  $X$  and  $Y$  has a cubic structure in which  $X$  atoms are at the corner of the cube and also at the face centers.  $Y$  atoms are present at the body centre and at the edge centre of the cube.

a. Calculate (i)  $Z_{eff}$ , (ii) total number of atoms in the cube, and (iii) formula of the compound.

b. If all the atoms are removed from one of the body diagonals of the cube, calculate (i)  $Z_{eff}$ , (ii) total number of atoms in the cube, and (iii) formula of the compound.

c. If all the atoms from the diagonals of the one of the face of the cube are removed, calculate (i)  $Z_{eff}$ ,

(ii) total number of atoms in the cube, and (iii) formula of the compound.

d. If all the atoms are removed from one of the plane passing through the middle of the cube, calculate (i)  $Z_{eff}$ , (ii) total number of atoms in the cube, and (iii) formula of the compound.

e. If all the atoms are removed from one of the axes passing through one of the face centres of the cube, calculate (i)  $Z_{eff}$ , (ii) total number of atoms in the cube, and (iii) formula of the compound.



[Watch Video Solution](#)

7. A compound formed by elements  $X$  and  $Y$  has a cubic structure in which  $X$  atoms are at the corner of the cube and also at alternate face centres.  $Y$  atoms are present at the body centre and also at the alternate edge centre of the cube.

a. Calculate (i)  $Z_{eff}$ , (ii) total number of atoms in the cube, and (iii) formula of the compound.

b. If all the atoms are removed from one of the plane passing through the middle of the cube of the cube which contains atoms both on the edge centre as well as on the face centre, calculate (i)  $Z_{eff}$ , (ii) total number of atoms in the cube, (iii) formula of the compound.



c. If all the atoms are removed from the plane passing through the middle of the cube which contains atoms only on the edge centre but not on face centre, calculate (i)  $Z_{eff}$ , (ii) total number of atoms in the cube, and (iii) formula of the compound.

d. If all the atoms are removed from one of the plane passing through the middle of the cube which neither contains atoms on the edge centre nor on the face centre, calculate (i)  $Z_{eff}$ , (ii) total number of atoms in the cube, and (iii) formula of the compound.

e. If all the atoms are removed from one of the axes passing through the middle of the cube containing

face centre atoms, calculate (i)  $Z_{eff}$ , (ii) total number of atoms in a cube, and (iii) formula of the compound.

f. If all the atoms are removed from one of the axes passing through the middle of the cube and not containing face centre atoms, calculate (i)  $Z_{eff}$ , (ii) total number of atoms in a cube, and (iii) formula of the compound.




[Watch Video Solution](#)

**8.** Draw a two-dimensional hexagonal lattice. Try to visualize the possibility of pentagonal two-dimensional lattice.




9. Consider the parallelograms shown in the figure below representing two-dimensional cells.



a. Which of these are primitive and which are multiple unit cells? Are any of these orthogonal?

c. What is the relation between the radius of circle and the length of parallelogram for the unit cell shown in the figure below (space filling diagram)?



d. How many nearest neighbour circles does a given circle have in the second figure above?

e. What is the radius of the triangular hole shown in the second figure above?

f. What is the packing fraction of the unit cell in the second figure above?

 [Watch Video Solution](#)

10. Why uncharged atoms or molecular never crystallize in simple cubic structures?

 [Watch Video Solution](#)

11. Why an end-centred unit cell cannot be cubic?  
What is the highest possible symmetry for this type of unit cell?

 [Watch Video Solution](#)

12. Why a hexagonal close-packed structure and a cubic close-packed structure for a given element

would be expected to have the same density?



Watch Video Solution

**13.** Select the close-packing arrangements in the following:

a. ... *ABABABA* ..., b. ... *ABCABCABCA* ...

c. ... *ABABCBCABC* ... , d. ... *ACCBCABCABC*

...



Watch Video Solution

14. A compound is formed by two elements  $X$  and  $Y$ . Atoms of the element  $Y$  (as anion) make ccp and those of element  $X$  (as cation) occupy all the octahedral voids. What is the formula of the compound?

 [Watch Video Solution](#)

15. Atoms of elements  $B$  from hcp lattice and those of element  $A$  occupy two-thirds of tetrahedral voids. What is the formula of the compound formed by elements  $A$  and  $B$ ?

 [Watch Video Solution](#)

16. An element has a bcc structure with a cell edge of 288 pm. The density of the element is  $7.2\text{gcm}^{-3}$ . How many atoms are present in 208g of the element?



Watch Video Solution

17. X-rays diffraction studies show that copper crystallizes in an fcc unit cell with cell edge of  $3.608 \times 10^{-8}\text{cm}$ . In a separate experiment, copper is determined to have a density of  $8.92\text{gcm}^3$ . Calculate the atomic mass of copper.



Watch Video Solution





Watch Video Solution

**18.** Silver forms ccp lattice and  $X$ -ray studies of its crystals show that the edge length of its unit cell is 408.6 pm. Calculate the density of silver (atomic mass = 107.9u).



Watch Video Solution

**19.** Metallic gold crystallizes in the fcc lattice.

The length of the cubic unit cell is  $a = 4.242\text{\AA}$ .

a. What is the closest distance between gold atoms?

b. How many "nearest neighbours" does each gold atom have at the distance calculated in (a)?

(c) What is the density of gold? ( $A_w$  of Au =  $197.0 \text{ g mol}^{-1}$ )

d. Prove that the packing factor for gold is 0.74.

 [Watch Video Solution](#)

**20.** If the radius of an atom of an element is 75 pm and the lattice type is body-centred cubic, what is the edge length of the unit cell?

 [Watch Video Solution](#)

21. The radius of an atom of an element is 500 pm. If it crystallizes as a face-centred cubic lattice, what is the length of the side of the unit cell?



[Watch Video Solution](#)

22. Sodium has a *bcc* structure with nearest neighbour distance of 365.9 pm. Calculate its density. (Atomic mass of sodium = 23)



[Watch Video Solution](#)

**23.** A face-centred cubic element (atomic mass 60) has a cell edge of 400 pm. What is its density?



**Watch Video Solution**

**24.** Xenon crystallizes in the face-centred cubic lattice and the edge of the unit cell is 620 pm. What is the nearest neighbour distance and what is the radius of xenon atom?



**Watch Video Solution**

25. In a compound, oxide ions are arranged in p. One-sixth of the tetrahedral voids are occupied by cations. ( $A$ ) and one-third of  $OV_s$  are occupied by cations ( $B$ ). (a) What is the formula of the compound of the compound? (b) What are the charges on  $A$  and  $B$  ?



[Watch Video Solution](#)

26. A compound is made of two elements  $P$  and  $Q$  are in p arrangement while atoms  $P$  occupy all the tetrahedral voids. What is the formula of the compound?



Watch Video Solution

27. Two ions  $A^{\oplus}$  and  $B^{\ominus}$  have radii 88 and 200 pm, respectively. In the close-packed crystal of compound  $AB$ , predict coordination number of  $A^{\oplus}$ .



Watch Video Solution

28. If the close-packed cations in an  $AB$ -type solid with NaCl structure gave a radius of 75 pm. What would be the maximum and minimum sizes of the anions filling the voids?



Watch Video Solution

29. If the radii of  $Mg^{2+}$ ,  $Cs^{\oplus}$ ,  $O^{2-}$ ,  $S^{2-}$ , and  $Cl^{\ominus}$  ions are 0.65, 1.69, 1.40, 1.84, and 1.81 Å, respectively, calculate the coordination number of the cation in the crystals of  $MgS$ ,  $MgO$ , and  $CsCl$ .



[Watch Video Solution](#)

30. Whenever two-dimensional square packing same layers are kept in the way so that the centres are aligned in all three dimension, coordination number of each sphere is

A. 6

B. 8

C. 12

D. 10

**Answer: A**






**Watch Video Solution**


**31.** In an  $f$  crystal, which of the following shaded planes contain the given ( $\rightarrow$ ) type of type of




arrangement of atoms?



C.



d.



D.

**Answer: A**



**Watch Video Solution**

**32.** In hexagonal close packing of spheres in three dimensions.

A. In one unit cell there are 12 octahedral voids and all are completely inside the unit cell.

B. In one unit cell there are six octahedral voids and all are completely inside the unit cell.

C. In one unit cell there are six octahedral voids and of which three are completely inside the unit cell and other three are from contributions of octahedral voids which are partially inside the unit cell

D. in one unit cell there are 12 tetrahedral voids, all are completely inside the unit cell.

**Answer: B**



**Watch Video Solution**

**33.** The coordination number of an  $f$  structure for a metal is 12, since

- A. Each atom touches four others in same layer,  
two in layer above and six in layer below
- B. Each atom touches four others in same layer,  
four in layer above and four in layer below.

C. Each atom touches six others in same layer,  
three in layer above and three in layer below

D. Each atom touches eight others in same layer,  
two in layer above and two in layer below.

**Answer: A**



**Watch Video Solution**

**34.** Which of the following statements is correct for a two-dimensional hexagonal close-packed layer?

A. Each sphere is surrounded by six spheres

B. Each sphere is surrounded by six voids

C. Each sphere has three voids





D. Each voids is surrounded by three spheres

**Answer: A::B::D**



**Watch Video Solution**

**35.** A compound made of particles  $A$ ,  $B$ , and  $C$  forms a lattice. Ions  $A$  are at lattice points,  $B$  occupy  $TV_s$ ,  $C$  occupy  $OV_s$ . If all the ions along one of the edge axis are removed, then formula of the compound is







**Answer: A**



**Watch Video Solution**

**36.** A compound made of particles  $A$ ,  $B$ , and  $C$  forms p lattice. In the lattice, ions  $A$  occupy the lattice points and ions  $B$  and  $C$  occupy the alternate  $TV_s$ . If all the ions along one of the body

diagonals are removed, then formula of the compound is






**Answer: A**



**Watch Video Solution**



37. A compound made of particles  $A$  and  $B$ .  $A$  forms  $fcc$  packing and  $B$  occupies all the  $OV_s$ . If all the particles along the plane as shown in the figure below are removed, then the simplest formula of the compound is



D.  $AB_{3.75}$

**Answer: C**



**View Text Solution**

**38.** In a solid having rock salt structure, if all the atoms touching one body diagonal plane are removed (except at body centre), then the formula of the left unit cell is

A.  $A_{3.5}B_{2.5}$

B.  $A_7B_3$

C.  $A_5B_3$

D.  $A_3B_5$

**Answer: A**



[Watch Video Solution](#)

**39.** Calculate the value of Avogadro's number from the following data:

Density of  $NaCl = 2.165 \text{ g cm}^{-3}$

Distance between  $Na^{\oplus}$  and  $Cl^{\ominus}$  in  $NaCl = 281$  pm



[Watch Video Solution](#)

40.  $CsCl$  has  $bcc$  arrangement and its unit cell edge length is 400 pm. Calculate the interionic distance in  $CsCl$ .



Watch Video Solution

41. A solid  $AB$  has  $CsCl$ -type structure. The edge length of the unit cell is 404 pm. Calculate the distance of closest approach between  $A^{\oplus}$  and  $B^{\ominus}$  ions.



Watch Video Solution

**42.**  $CsCl$  has cubic structure. Its density is  $3.99\text{gcm}^{-3}$ . What is the distance between  $Cs^{\oplus}$  and  $Cl^{\ominus}$  ions?


(Atomic mass of  $Cs = 133$ )



**Watch Video Solution**

**43.** The unit cube length for  $LiCl$  ( $NaCl$  structure) is  $5.14\text{\AA}$ . Assuming anion-anion contact, calculate

the ionic radius for chloride ion.



[Watch Video Solution](#)

44. Cesium may be considered to form interpenetrating simple primitive cubic crystal. The edge length of unit cell is 412 pm. Determine

a. The density of  $CsCl$ .

b. The ionic radius of  $Cs^{\oplus}$  if the ionic radius of  $Cl^{\ominus}$

is 181 pm. Given:  $A_w(Cs) = 133 \text{ g mol}^{-1}$



Watch Video Solution

45.  $KCl$  crystallizes in the same type of lattice as does  $NaCl$ . Given that

$$\frac{r_{Na^{\oplus}}}{r_{Cl^{\ominus}}} = 0.5 \text{ and } \frac{r_{Na^{\oplus}}}{r_{K^{\oplus}}} = 0.7$$

Calculate (a) the ratio of side of the unit cell for  $KCl$  to that for  $NaCl$ , and (b) the ratio of density of  $NaCl$  to that  $KCl$ .



Watch Video Solution

46.  $LiI$  occurs as cubical closed packing. If the edge length of unit cell is 624 pm, determine the ionic radii of  $Li^{\oplus}$  and  $I^{\ominus}$  ions.

 [Watch Video Solution](#)

47. The composition of a sample of Wustite is  $Fe_{0.93}O_{1.00}$ . What percentage of the iron is present in the form of  $Fe(III)$ ?

 [Watch Video Solution](#)



48.  $CsBr$  crystallizes in a body-centred cubic unit lattice with an edge length of  $4.287\text{\AA}$ . Calculate the angles at which the second-order reflection maxima may be expected for  $(2, 0, 0)$ ,  $(1, 1, 0)$ , planes when  $X$ -rays of  $\lambda = 0.50\text{\AA}$  are used.

 [Watch Video Solution](#)

49. Calculate the miller indices of crystal. Planes which cut through the crystal axes at

A.  $(2a, 3b, c)$

B.  $(a, b, c)$

C.  $(6a, 3b, 3c)$

D.  $(2a, -3b, -3c)$

**Answer:**



**Watch Video Solution**

**50.** How do the spacings of the three planes 100, 110, and 111 of cube lattice vary?



**Watch Video Solution**

51. Potassium chloride crystallize with a body-centred cubic lattice. Calculate the distance between the 200, 110, and 222 Planes. The length of the side of the unit cell is  $5.34\text{\AA}$ .

 [Watch Video Solution](#)

52. Diamond has face-centred cubic lattice. There are two atoms at  $(0, 0, 0)$  and  $\left(\frac{a}{4}, \frac{a}{4}, \frac{a}{4}\right)$  coordinates. The ratio of the carbon-carbon bond distance to the edge of the unit cell is

A.  $\sqrt{\frac{3}{16}}$

B.  $\sqrt{\frac{1}{4}}$

C.  $\frac{1}{4}$

D.  $\frac{1}{\sqrt{2}}$

**Answer: A**



**Watch Video Solution**

**53.** Which of the following statements is(are) correct for the diamond structure?

A. Each atom has 4 nearest neighbours and 12 next nearest neighbours.

B. It is relatively empty.

C. The maximum proportion of the available volume which may be filled by hard spheres is only 0.34.

D. The maximum proportion of the available volume which may be filled by hard sphere is only 0.46.

**Answer: A::B::C**



**Watch Video Solution**

54. Which of the following compounds are not isomorphous?

a. Copper sulphate and zinc sulphate

b. Zinc sulphate and manganese sulphate

c. Calcium carbonate and ferrous sulphate d. Zinc sulphate and ferrous sulphate



[Watch Video Solution](#)

55. Potassium selenate is isomorphous with potassium sulphate and contains 50.0% of *Se*. The atomic weight of *Se* is

a. 142, b. 71, c. 47.33, d. 284



Watch Video Solution

56. The  $Ew$  of an element is 13. It forms an acidic oxide which  $KOH$  forms a salt isomorphous with  $K_2SO_4$ . The  $Aw$  of element is

a. 13, b. 26, c. 52, d. 78



Watch Video Solution

57. If  $NaCl$  is doped with  $10^{-2} mol\%$   $SrCl_2$ , what is the concentration of the cation vacancies?



Watch Video Solution

58. If  $NaCl$  is doped with  $10^{-3} mol \% GaCl_3$ , what is the concentration of the cation vacancies?



Watch Video Solution

59. If all the atoms touching one face plane are removed in solid  $A^{\oplus}B^{\ominus}$  having rock salt type structure, then the formula of the compound left and the defect brought by this removal, respectively, is

A.  $AB$ , Frenkel defect

B.  $A_2B$ , Frenkel defect



C.  $AB$ , Schottky defect

D.  $A_2B$ , Schottky defect

**Answer: C**



[Watch Video Solution](#)

**60.** The addition of  $CaCl_2$  crystal to  $KCl$  crystal

a. Lowers the density of the  $KCl$  crystal

b. Raises the density of the  $KCl$  crystal

c. Does not affect the density of the  $KCl$  crystal

d. Increases the Frenkel defects of the  $KCl$  crystal



[Watch Video Solution](#)

**61.** What fraction of the surface of a crystal of  $Cd$  at  $T = 298K$  consists of vacancies? Assume that the energy needed to form a vacancy  $= 0.5\Delta_{\text{sub}}H^{\ominus}$ . For  $Cd(s)$ ,  $\Delta_{\text{sub}}H^{\ominus} = 112.0kJmol^{-1}$ .

 [Watch Video Solution](#)

**62.** Calcium crystallizes in  $f$  unit cell with  $0.556nm$ .

Calculate the density if

a. It contains 0.2 % Frenkel defects

b. It contains 0.1 % Schottky defects

 [Watch Video Solution](#)

## Solved Examples

1. The pyknometric density of  $NaCl$  crystal is  $2.165 \times 10^3 kgm^{-3}$  while its  $X$ -ray density is  $2.178 \times 10^{-3} kgm^{-3}$ . The fraction of unoccupied sites in  $NaCl$  crystal is

a. 5.96 b.  $5.96 \times 10^{-2}$

c.  $5.96 \times 10^{-1}$  d.  $5.96 \times 10^{-3}$



[Watch Video Solution](#)

2. The molar volumes of  $KCl$  and  $NaCl$  are  $40mL$  and  $30mL$ , respectively. Find the ratio of the unit cube edges of the two crystals. Assume both have the same packing efficiency.



[Watch Video Solution](#)

3. Calculate the void space in closest packing of  $n$  spheres of radius 1 unit,  $n$  spheres of radius 0.414 units, and  $2n$  spheres of radius 0.225 units.



[Watch Video Solution](#)

4. Calculate the following:

a. Number of  $ZnS$  units in a unit cell of zinc blende.

b. Number of  $CaF_2$  unit cell of  $CaF_2$ .



[Watch Video Solution](#)

5. If the length of the body for  $CaCl$  which crystallizes into a cubic structure with  $Cl^{\ominus}$  ions at the corners and  $Ca^{\oplus}$  ions at the centre of the unit cell is  $7\text{\AA}$  and the radius of the  $Ca^{\oplus}$  ions is  $1.69\text{\AA}$ , what is the radius of  $Cl^{\ominus}$  ions?



[Watch Video Solution](#)

6. For a cubic crystal, the face diagonal is  $3.5\text{\AA}$ . Calculate the face length.

 [Watch Video Solution](#)

7. Cesium chloride forms a body-centred cubic lattice. Cesium and chloride ions are in contact along the body diagonal of a cell. The length of the side of the unit cell is  $412 \pm$  and  $Cl^{\ominus}$  ion has a radius of  $181 \text{ pm}$ . Calculate the radius of  $Cs^{\oplus}$  ion.

 [Watch Video Solution](#)

8. A unit of cell of sodium chloride has four formula units. The edge length of the unit cell is  $0.564\text{nm}$ . What is the density of sodium chloride?

 [Watch Video Solution](#)

9. In an  $LiI$  crystal,  $I^{\ominus}$  ions form a cubical close-packed arrangement, and  $Li^{\oplus}$  ions occupy octahedral holes. What is the relationship between the edge length of the unit cells and radii of the  $I^{\ominus}$  ions if  $a = 60\text{pm}$ ?

 [Watch Video Solution](#)

10. An element occurs in two crystalline form  $\alpha$  and  $\beta$ . The  $\alpha$ -form has an  $f$  with  $a = 3.68\text{\AA}$  and  $\beta$ -form has a  $b$  with  $a = 2.92\text{\AA}$ . Calculate the ratio of their densities.



Watch Video Solution

11. Find the simplest formula of a solid containing  $A$  and  $B$  atoms in cubic arrangement in which  $A$  occupies corner and  $B$  the centre of the faces of unit cell. If the side length is  $5\text{\AA}$ , estimate the density of the solid assuming atomic weights of  $A$  and  $B$  as 60 and 90, respectively.





Watch Video Solution

12. In the cubic crystal of  $CsCl$  ( $d = 3.97 \text{ g cm}^{-3}$ ), the eight corners are occupied by  $Cl^{\ominus}$  with a  $Cs^{\oplus}$  at the centre and vice versa. Calculate the distance between the neighbouring  $Cs^{\oplus}$  and  $Cl^{\ominus}$  ions. What is the radius of the two ions? ( $A_w$  of  $Cs = 132.91$  and  $Cl = 35.45$ )



Watch Video Solution

13.  $Li$  forms a body-centred cubic lattice. If the edge of the cube is  $3.5 \times 10^{-10} \text{ m}$  and the density is

$5.3 \times 10^2 \text{ kgm}^{-3}$ , calculate the percentage occupancy of *Li* metal.



Watch Video Solution

## Exercises Linked Comprehension

1. If calcium crystallizes in *bcc* arrangement and the radius of *Ca* atom is  $96 \pm$ , then the volume of unit cell of *Ca* is

A.  $10.9 \times 10^{-36} \text{ m}^3$

B.  $10.9 \times 10^{-30} \text{ m}^3$

C.  $21.8 \times 10^{-30} m^3$

D.  $21.8 \times 10^{-36} m^3$

**Answer: B**



**Watch Video Solution**

2. The number of unit cells in the  $Ca$  atom lies on the surface of a cubic crystal that is  $1.0\text{cm}$  in length is

A.  $9.17 \times 10^{23}$

B.  $9.17 \times 10^{22}$

C.  $2 \times 9.17 \times 10^{23}$

D.  $2 \times 9.17 \times 10^{22}$

**Answer: B**



**Watch Video Solution**

3. The fraction of  $Ca$  atoms that lies on the surface of a cubic crystal that is  $1.0\text{cm}$  in length is

A.  $1.11 \times 10^{-8}$

B.  $2.22 \times 10^{-8}$

C.  $1.11 \times 10^{-7}$

$$D. 2.22 \times 10^{-7}$$

**Answer: A**





**Watch Video Solution**

4. The OLIVINE series of minerals consists of crystal in which  $Fe^{2+}$  and  $Mg^{2+}$  ions may substitute for each other causing substitutional impurity defects without changing the volume of unit cell. In OLIVINE series of minerals,  $O^{2-}$  ions exist as fcc with  $Si^{4+}$  occupying one-fourth of  $OVs$  and divalent metal ions occupying one-fourth of  $OVs$  and divalent metal ions occupying one-fourth

of  $TV_s$ . The density of "forsterite" (magnesium silicate) is  $3.21\text{gcm}^{-3}$  and that of "fayalite" (ferrous silicate) is  $4.34\text{gcm}^{-3}$ .

The formula of "fayalite mineral" is



**Answer: A**







**Watch Video Solution**

5. The OLIVINE series of minerals consists of crystal in which  $Fe^{2+}$  and  $Mg^{2+}$  ions may substitute for each other causing substitutional impurity defects without changing the volume of unit cell. In OLIVINE series of minerals,  $O^{2-}$  ions exist as fcc with  $Si^{4+}$  occupying one-fourth of  $OV_s$  and divalent metal ions occupying one-fourth of  $OV_s$  and divalent metal ions occupying one-fourth of  $TV_s$ . The density of "forsterite" (magnesium silicate) is  $3.21gcm^{-3}$  and that of "fayalite" (ferrous silicate) is  $4.34gcm^{-3}$ .

If in "forsterite mineral" bivalent  $Mg^{2+}$  ions are to be replaced by unipositive  $Na^{\oplus}$  ions, and if  $Na^{\oplus}$  ions are occupying half of  $TV_s$  in  $f$  lattice, the

arrangement of rest of the constituents is kept same, then the formula of the new solid is:



**Answer: C**



**Watch Video Solution**



6.  $AX$ ,  $AY$ ,  $BX$ , and  $BY$  have rock salt type structure with following internuclear distances:

Salt	Anion-anion distance in Å	Cation-anion distance in Å
$AX$	2.40	1.70
$AY$	1.63	1.15
$BX$	2.66	1.88
$By$	2.09	1.48

Ionic radii of  $A^{\oplus}$  and  $B^{\oplus}$ , respectively, are

A. 0.35 and 0.68 Å

B. 0.68 and 0.35 Å

C. 1.20 and 0.80 Å

D. 0.80 and 1.20 Å

Answer: A



Watch Video Solution

7.  $AX$ ,  $AY$ ,  $BX$ , and  $BY$  have rock salt type structure with following internuclear distances:

Salt	Anion-anion distance in Å	Cation-anion distance in Å
$AX$	2.40	1.70
$AY$	1.63	1.15
$BX$	2.66	1.88
$By$	2.09	1.48

Ionic radii of  $X^{\oplus}$  and  $Y^{\ominus}$ , respectively, are

A. 0.35 and 0.68 Å

B. 0.68 and 0.35 Å

C. 1.20 and 0.80Å

D. 0.80 and 1.20Å

**Answer: C**




**Watch Video Solution**

8.  $AX$ ,  $AY$ ,  $BX$ , and  $BY$  have rock salt type structure with following internuclear distances:

Salt	Anion-anion distance inÅ	Cation-anion distance inÅ
$AX$	2.40	1.70
$AY$	1.63	1.15
$BX$	2.66	1.88
$By$	2.09	1.48

The structure given below is of



A.  $AX$

B.  $AY, BX$

C.  $AY, BX, BY$

D.  $AY, BX, BY$  and  $KCl$

Answer: D







Watch Video Solution

9.  $AX$ ,  $AY$ ,  $BX$ , and  $BY$  have rock salt type structure with following internuclear distances:

Salt	Anion-anion distance in Å	Cation-anion distance in Å
$AX$	2.40	1.70
$AY$	1.63	1.15
$BX$	2.66	1.88
$By$	2.09	1.48

Which of the following structure is, respectively, by  $Ax$ ?





**Answer: A**



**Watch Video Solution**

10.  $AX$ ,  $AY$ ,  $BX$ , and  $BY$  have rock salt type structure with following internuclear distances:

Salt	Anion-anion distance in Å	Cation-anion distance in Å
$AX$	2.40	1.70
$AY$	1.63	1.15
$BX$	2.66	1.88
$By$	2.09	1.48

A salt  $MY$  crystallizes in the  $CsCl$  structure. The anions at the corners touch each other and cation is in the centre. The radius ratio ( $r_{\oplus} / r_{\ominus}$ ) for this structure is

A. 0.225

B. 0.414

C. 0.732

D. 1.0

**Answer: C**






**Watch Video Solution**

**11.** In a unit cell, atoms ( $A$ ) are present at all corner lattices, ( $B$ ) are present at alternate faces and all edge centres. Atoms ( $C$ ) are present at face centres left from ( $B$ ) and one at each body diagonal at distance of  $1/4$ th of body diagonal from corner.

Formula of given solid is





**Answer: B**



**Watch Video Solution**

**12.** In a unit cell, atoms ( $A$ ) are present at all corner lattices, ( $B$ ) are present at alternate faces and all edge centres. Atoms ( $C$ ) are present at face centres left from ( $B$ ) and one at each body diagonal at

distance of  $1/4$ th of body diagonal from corner.

A tetrad axis is passed from the given unit cell and all the atoms touching the axis are removed. The possible formula of the compound left is

- A.  $AB_3C_6$  and  $AB_4C_5$
- B.  $A_3B_6C_7$  and  $A_3B_6C_5$
- C.  $A_4B_5C_8$  and  $A_4B_5C_7$
- D.  $AB_2C$  and  $ABC_2$

**Answer: A**



**Watch Video Solution**

13. In a unit cell, atoms ( $A$ ) are present at all corner lattices, ( $B$ ) are present at alternate faces and all edge centres. Atoms ( $C$ ) are present at face centres left from ( $B$ ) and one at each body diagonal at distance of  $1/4$ th of body diagonal from corner.

Total fraction of voids occupied are

A. 0.58

B. 0.25

C. 0.48

D. 0.86

**Answer: A**



**Watch Video Solution**

## Exercises Multiple Correct

1. Position of  $OV_s$  in an  $f$  structure is

- A. Corners of unit cell
- B. Edge centre of unit cell
- C. Body centre of unit cell
- D. Face centre of unit cell

**Answer: B::C**



**Watch Video Solution**

2. An hcp and a ccp structure for a given element would be expected to have

- A. The same coordination number
- B. The same density
- C. The same packing fraction
- D. All of these

**Answer: A::C**



**Watch Video Solution**

3. Ions of  $NaCl$  which are touched by 1 body diagonal are

- A.  $Cl^{\ominus}$  ions present at the corner of cube
- B.  $Cl^{\ominus}$  ions present at the face centre of cube
- C.  $Na^{\oplus}$  ions present at the edge centre of cube
- D.  $Na^{\oplus}$  ions present at body centre of cube

**Answer: A::D**



**Watch Video Solution**

4. Which of the following statements is/are correct for both fluorite and antifluorite structures?

- A. Cation is present in alternate  $TV_s$
- B. Anion constitutes lattice.
- C. Number of formula unit in one unit cell is 4.
- D. 100 % tetrahedral voids are occupied

**Answer: C::D**



**Watch Video Solution**

5. Identical spheres are undergoing two-dimensional packing in square close packing and hexagonal close packing. Which is correct regarding the spheres?

- A. The ratio of coordination number for a sphere in first case to that in second case is 2:3.
- B. Packing in second case is more effective.
- C. Packing in first case is more effective.
- D. The stacking of layer on first type packing produces simple cubic structure.

**Answer: A::B::D**





6. For which of the following cases, answer is 4

A. Coordination number of  $Zn^{2+}$  in  $Zn$  inc  
blende

B. Number of body diagonal planes in a cube

C. Formula units in rock salt structure

D. Formula units in  $CsCl$  structure

**Answer: A::C**



7. An octahedron has

A. 8 corners

B. 8 faces

C. 8 edges

D. 8 edges

**Answer: B::D**



**Watch Video Solution**

8. Aluminium metal has a density of  $2.72\text{gcm}^{-3}$  and crystallizes in a cubic lattice with an edge of 404 pm.

Which is//are correct?

- A. It forms an fcc unit cell.
- B. It forms a bcc unit cell.
- C. Its coordination number is 8.
- D. Its coordination number is 12.

**Answer: A::D**



**Watch Video Solution**

9. For the spinel structure ( $MgAl_2O_4$ ), the correct statement is//are

- A. 50 %  $OV_s$  are occupied by ions.
- B.  $Al^{3+}$  is equally distributed in  $TV_s$  and  $OV_s$ .
- C. Oxide ions occupy ccp lattice.
- D. 12.5 %  $TV_s$  are occupied by ions.

**Answer: A::C::D**



**Watch Video Solution**

**10.** If the radius of anion is  $0.20nm$ , the maximum radius of cation which can be filled in respective voids is correctly matched in

A.  $r_{\oplus} = 0.0828nm$  for tetrahedral void

B.  $r_{\oplus} = 0.045nm$  for triangular void

C.  $r_{\oplus} = 0.1464nm$  for tetrahedral void

D. None of the above.

**Answer: A::B::C**



**Watch Video Solution**

11. Which of the following statements is/are correct?

A. Dislocation of ion from lattice site to interstitial site is called Frenkel defect.

B. Missing of  $+ve$  and  $-ve$  ions from their respective position producing a pair of holes is called Schottky defect.

C. The presence of ions in the vacant interstitial sites along with lattice point is called interstitial defect.

D. Non-stoichiometric  $NaCl$  is yellow solid.

**Answer: A::B::C::D**



**Watch Video Solution**

12. Select the correct statement(s).

- A. The conductance through electron is called  $p$ -type conduction.
- B. The conductance through positive holes is called  $p$ -type conduction.
- C. The conductance through electrons is called  $n$ -type conduction.
- D. The band gap in germanium is small.

**Answer: B::C::D**

13. Select the correct statement(s).

A. Solids with  $F$ -centres are paramagnetic.

B. Ferrimagnetic character of  $Fe_3O_4$  at room temperature changes to paramagnetic character at  $850K$ .

C. Anti-ferrimagnetic  $V_2O_3$  changes to paramagnetic at  $150K$ .

D. Non-stoichiometric  $Cu_2O$  is a  $p$ -type semiconductor.



Answer: A::B::C::D



Watch Video Solution

14. Select the correct statement(s) about three-dimensional *hcp* system.

A. The number of atoms in *hcp* unit cell is six.

B. The volume of *hcp* unit cell is  $24\sqrt{2}r^3$ .

C. The empty space in *hcp* unit cell is 26 % .

D. The base area of *hcp* unit is  $6\sqrt{3}r^2$ .

Answer: A::B::C::D



Watch Video Solution

15. In which of the following system primitives

$$a \neq b \neq c?$$

A. Orthorhombic

B. Monoclinic

C. Triclinic

D. Hexagonal

**Answer: A::B::C**



Watch Video Solution

16. In which of the following systems interfacial angles  $\alpha = \gamma = 90^\circ$  but  $\beta \neq 90^\circ$ ?

- A. Monoclinic
- B. Rhombohedral
- C. Triclinic
- D. Hexagonal

**Answer: A::B**



**Watch Video Solution**

17. The space in which atoms are not present in unit cell is

A. In sc 48 %

B. In fcc 26 %

C. In bcc 32 %

D. In hexagonal 26 %

**Answer: A::B::C::D**



**Watch Video Solution**

18. Which of the following having having their radius ratio between 0.414 and 0.732, i.e., for  $NaCl$  structure, have their radius ratio not in this range but posses  $NaCl$ -type structure?

A. LiBr

B. KCl

C. RbCl

D. BaO

**Answer: A::B::C::D**



**Watch Video Solution**

19. In the fluorite structure if the radius ratio is

$\left(\frac{\sqrt{3}}{2} - 1\right)$  how many ions does each cation

touch?

A. 4 anions

B. 12 cations

C. 8 anions


D. No cations

**Answer: B::C**



**Watch Video Solution**

20. Following three planes ( $P_1, P_2, P_3$ ) in an fcc unit cell are shown in the figure below. Consider the following statements and choose the correct option/options that follow:



- A.  $P_1$  contains no three-dimensional voids.
- B.  $P_2$  contains only octahedral voids.
- C.  $P_3$  contains both octahedral and tetrahedral voids
- D. All of these

Answer: A::B::C::D



Watch Video Solution

21. If the radius of  $Cs^{\oplus} = 1.69\text{\AA}$  and  $Br^{\ominus} = 1.95\text{\AA}$ , then which of the following is//are correct statement?

A. The edge length of unit cell is  $4.2\text{\AA}$ .

B. The coordination number for  $Cs^{\oplus}$  is 6.

C.  $CsBr$  has bcc-type structure.

D.  $Br^{\ominus}$  ions touch each other along the edge.



**Answer: A::C**




**Watch Video Solution**

22. Given is the arrangement of atoms in a crystallographic plane.

Which plane correctly represent(s) the adjacent

drawn structure?



A. Face plane in fcc

B. Body diagonal plane in fcc

C. Face plane in bcc

D. Body diagonal plane in bcc

**Answer: A::D**



**Watch Video Solution**

**23.** Position of octahedral voids in fcc structure is//are

- A. Edge centre of unit cell
- B. Body centre of unit cell
- C. Corners of unit cell
- D. Face centre of unit cell

**Answer: A::B**

 Watch Video Solution

24. Position of  $TVs$  in closest packed structure is//are

- A. Edge centre of unit cell
- B. Two  $TVs$  on each body diagonal
- C. Position of each  $TV$  from corner is  $\sqrt{3}a/4$ .
- D. Face centre of unit cell

**Answer: B::C**

 Watch Video Solution

25. Which of the following statements is/are correct about  $TVs$  in an fcc unit cell?

A. Number of  $TVs$  per atom in fcc unit cell is 2.

B. Number of  $TVs$  per unit cell is 8.

C. Number of  $TVs$  is twice the number of atoms in the fcc unit cell.

D. Number of  $TVs$  is equal to the number of atoms in the fcc unit cell?

**Answer: A::B::C**



**Watch Video Solution**

26. Which of the following statements is//are correct about  $TV$ s in an fcc unit cell?

Given: Edge length =  $a$

Body diagonal =  $b$

- A. Each  $TV$  lies at a distance  $b/4$  from the nearest corner.
- B. Each  $TV$  lies at a distance  $3b/4$  from the farthest corner.
- C. Each  $TV$  lies at a distance of  $\sqrt{3}a/4$  from the nearest corner.

D. The distance between two  $TV_s$  is  $b/2$ .

**Answer: A::B::C::D**



**Watch Video Solution**

## 27. Graphite

- A. A good conductor
- B.  $sp^2$  hybridized
- C. An amorphous solid
- D. A covalent crystal

**Answer: A::B::D**



**Watch Video Solution**

**28. Diamond**

- A. A covalent solid
- B. A non-conductor
- C. A lubricant
- D.  $sp^3$  hybridized

**Answer: A::B::D**



**Watch Video Solution**



29. The density of  $KBr$  is  $2.75\text{gcm}^{-3}$ . The length of the unit cell is 654 pm. Atomic mass of  $K = 39$ ,  $Br = 80$ . Then what is true about the predicted nature of the solid?

A. The unit cell is fcc.

B.  $Z = 4$ .

C. There are four constituents/unit cells.

D. There are 8 ions at corners and 6 at the centres of the faces.

**Answer: A::B::C::D**



Watch Video Solution

30. What is true about a bcc unit cell?

- A. The number of atoms in the unit cell is 2.
- B. In addition to an atom at the centre of the body, in a unit cell there are 8 atoms at 8 different corners.
- C. One-eighth of an atom at a corner of the unit cell.
- D. None of the above.

Answer: A::B::C



Watch Video Solution

31. What is true about simple cubic type of unit cells?

A. Eight constituents are at different corners of the cube.

B.  $Z_{eff} = 1$ .

C. Contribution by one corner is  $(1) / (8)th$  of an atom`.

D. None of the above.

**Answer: A::B::C**



**Watch Video Solution**

**32. Which of the following is//are covalent solids?**

A. *Fe*

B. Diamond

C. *NaCl*

D. Graphite

**Answer: B::D**



**Watch Video Solution**

**33. Which is/are not amorphous solid(s)?**

A. Rubber

B. Graphite

C. Glass



D. Plastics

**Answer: B**



**Watch Video Solution**

34. Non-stoichiometric compounds are






Answer: A::B::C::D



Watch Video Solution

35. Recently discovered superconductivity materials are



**Answer: A::B::D**



**Watch Video Solution**

36. If a mixture of  $LiCl$  and  $NaCl$  is melted and then cooled,

- A. A solid solution is formed.
- B. Mixture formed is called eutectic mixture.
- C.  $TiO_{1.8}$  is non-stoichiometric solid solution of  $Ti_2O_3$  and  $TiO_2$ .
- D. Neither  $LiCl$  nor  $NaCl$  separates.

**Answer: A::B::C::D**



**Watch Video Solution**



37. Which of the following statements is/are correct?

- A. If three  $Fe^{2+}$  ions are missing from their lattice in  $FeO$ , then there must be two  $Fe^{3+}$  ions somewhere in the lattice.
- B. Crystals with metal deficiency defects are called super conductors.
- C. Crystals with metal deficiency are called semiconductors.
- D. 1 Bohr Magneton =  $9.27 \times 10^{-24} Am^2$

**Answer: A::C::D**



Watch Video Solution

38. Select the correct statement(s).

A. The non-stoichiometric form of  $NaCl$  is yellow and that of  $KCl$  is blue-lilac.

B. Solids containing  $F$ -centres (Farbe) are paramagnetic.

C. Non-stoichiometric compounds are called Berthollide compounds.

D. Conduction by electrons is called  $n$ -type semiconductor.

Answer: A::B::C::D



Watch Video Solution

39. A mineral having the formula  $AB_2$  crystallizes in the p lattice, with  $A$  atoms occupying the lattice points. Select the correct statement(s).

- A. The coordination number ( $CN$ ) for  $A$  atoms = 8.
- B. The  $CN$  for  $B$  atom = 4
- C. 100 % of  $TV_s$  are occupied by  $B$  atoms
- D. 50 % of  $TV_s$  are occupied by  $B$  atoms.

Answer: A::B::C






Watch Video Solution

## Exercises Single Correct

1. A crystal is made up of particles  $X$ ,  $Y$ , and  $Z$ .  $X$  forms  $f$  packing.  $Y$  occupies all octahedral voids of  $X$  and  $Z$  occupies all tetrahedral voids of  $X$ . If all the particles along one body diagonal are removed. Then the formula of the crystal would be

A.  $XYZ_2$




**Answer: D**




**Watch Video Solution**

2. In a hypothetical solid,  $C$  atoms are found to form cubical close-packed lattice.  $A$  atoms occupy all tetrahedral voids and  $B$  atoms occupy all octahedral voids.




$A$  and  $B$  atoms are of appropriate size, so that there is no distortion in the p lattice of  $C$  atoms. Now if a plane as shown in the following figure is cut, then the cross section of this plane will look like

a.




A.

B. 



C.



D.

**Answer: C**



**Watch Video Solution**

3. What is the maximum number of layers of atom in close-packed planes that will lie within two imaginary parallel planes having a distance between them of  $13\sqrt{\frac{2}{3}}r$  (where  $r$  is the radius of atom) in the copper crystal (fcc)?

(Consider the atoms to be within the parallel planes if their centres are on or within the two parallel planes).

A. 5

B. 6

C. 7

D. 8




**Answer: C**



**Watch Video Solution**

4. Analysis show that nickel oxide consists of nickel ion with 96 % ions having  $d^8$  configuration and 4 % having  $d^7$  configuration. Which amongst the following best represents the formula of the oxide?



**Answer: D**



**Watch Video Solution**

5. What is the density of  $Na_2O$  having antifluorite-type crystal structure, if the edge length of cube is  $100\text{Å}$  and what is the effect on density by 0.05 % Frenkel defect?

- A.  $823.5\text{gcm}^{-3}$ , density decreases
- B.  $4.14.16\text{gcm}^{-3}$ , density decreases
- C.  $823.5\text{gcm}^{-3}$ , density remains same
- D.  $414.16\text{gcm}^{-3}$ , density remains same

**Answer: D**



**Watch Video Solution**

**6.** In the calcium fluoride structure, the coordination number of the cation and the anion are, respectively,

A. 6 and 6

B. 8 and 4

C. 4 and 4

D. 4 and 8

**Answer: B**



**Watch Video Solution**

7. A metallic crystal crystallizes into a lattice containing a sequence of layers  $ABABAB\dots$ . Any packing of spheres leaves out voids in the lattice. What percentage by volume of this lattice is empty space?

A. 74 %

B. 26 %

C. 50 %

D. None of these


**Answer: B**



**Watch Video Solution**

8. In an f.c.c unit cell , atoms are numbered as shown below . The atoms not touching each other

are (Atom numbered 3 is face centre of front face )



A. 3 and 4

B. 1 and 3

C. 1 and 2




D. 2 and 4

Answer: C



Watch Video Solution

9. The number of nearest neighbours and next nearest neighbours of an  $Na^{\oplus}$  ion in a crystal of  $NaCl$  are, respectively,



**Answer: B**



**Watch Video Solution**

**10.** In the closest packing of atoms

- A. The size of  $TV$  is greater than that of  $OV$ .
- B. The size of  $TV$  is smaller than that of  $OV$ .
- C. The size of  $TV$  is equal to that of  $OV$ .
- D. The size of  $TV$  may be greater or smaller or equal to that of  $OV$  depending upon the size of atoms.




Answer: B



Watch Video Solution

11. The following diagram shows the arrangement of lattice points with  $a = b = c$  and  $\alpha = \beta = \gamma = 90^\circ$ . Choose the correct options.



- A. The arrangement is *sc* with each lattice point surrounded by 6 nearest neighbours.
- B. The arrangement is *sc* with each lattice point surrounded by 8 nearest neighbours.
- C. The arrangement is *fcc* with each lattice point surrounded by 12 nearest neighbours.
- D. The arrangement is *bcc* with each lattice point surrounded by 8 nearest neighbours

**Answer: A**



**Watch Video Solution**

12. The number of atoms in 100g of an fcc crystal with density =  $10.0\text{gcm}^{-3}$  and cell edge equal to  $200 \text{ \AA}$  is equal to

A.  $5 \times 10^{24}$

B.  $5 \times 10^{25}$

C.  $6 \times 10^{23}$

D.  $2 \times 10^{25}$

**Answer: A**



**Watch Video Solution**

13. Due to Frenkel defect, the density of the ionic solids

- A. Increases
- B. Decreases
- C. Does not change
- D. Changes

**Answer: C**



**Watch Video Solution**

14. In a tetragonal crystal

A.  $a = b = c, \alpha = \beta = 90^\circ \neq \gamma$

B.  $\alpha = \beta = \gamma = 90^\circ, a = b \neq c$

C.  $\alpha = \beta = \gamma = 90^\circ, a \neq b \neq c$

D.  $\alpha = \beta = 90^\circ, \gamma = 120^\circ, a = b \neq c$



**Answer: B**



**Watch Video Solution**

**15.** Which of the following is not a ferroelectric compound?

A. Rochelle salt



**Answer: B**



**Watch Video Solution**

**16.** The material used in solar cells contains



D.  $Ti$

**Answer: B**



**Watch Video Solution**

17. In the lattice parameter of  $Si = 5.43\text{\AA}$  and the mass of  $Si$  atom is  $28.08 \times 1.66 \times 10^{-27} \text{kg}$ , the density of silicon in  $\text{kgm}^{-3}$  is (Given: Silicon has diamondcubic structure)

A. 2330

B. 1115

C. 3445

D. 1673

**Answer: A**



**Watch Video Solution**

**18.** The lattice parameter of  $GaAs$  (radius of  $Ga = 1.22\text{\AA}$ ,  $As = 1.25\text{\AA}$ ) is

A.  $5.635\text{\AA}$

B.  $2.852\text{\AA}$

C.  $5.774\text{\AA}$



D.  $4.94\text{\AA}$

**Answer: B**



**Watch Video Solution**

19. In cubic  $ZnS(II - VI)$  compounds, if the radii of  $Zn$  and  $S$  atoms are  $0.74\text{\AA}$  and  $1.70\text{\AA}$ , the lattice parameter of cubic  $ZnS$  is

A.  $11.87\text{\AA}$

B.  $5.634\text{\AA}$

C.  $5.14\text{\AA}$

D.  $2.97\text{\AA}$

**Answer: B**



**Watch Video Solution**

20. *Na* and *Mg* crystallize in bcc- and fcc-type crystals, the ratio of number of atoms present in the unit cell of their respective crystal is

A. 1

B. 0.5

C. 3

D. 4


**Answer: B**



**Watch Video Solution**

21. In a closed packed structure of mixed oxides, the lattice is composed of mixed oxides ions. One-eighth of tetrahedral voids are occupied by divalent cation ( $A^{2+}$ ) while one-half of octahedral voids are occupied by trivalent cations ( $B^{3+}$ ). The formula of mixed oxide is

A.  $A_2BO_3$



**Answer: D**



**Watch Video Solution**

22. An ionic solid  $A^{\oplus}B^{\ominus}$  crystallizes as an bcc structure. The distance between cation and anion in the lattice is  $338 \pm$  . The edge length of cell is

A. 338 pm

B. 390.3 pm

C. 292.7 pm

D. 507 pm

**Answer: B**



**Watch Video Solution**

23. An ionic solid  $A^{\oplus}B^{\ominus}$  crystallizes as an fcc structure. If the edge length of cell is 508 pm and the radius of anion is  $144 \pm$ , the radius of cation is

A. 110 pm

B. 364 pm

C. 220 pm

D. 288 pm

**Answer: A**



**Watch Video Solution**

**24.** The  $\gamma$ -form of iron has  $f$  structure (edge length  $386 \pm$  ) and  $\beta$ -form has  $b$  structure (edge length  $290 \pm$  ). The ratio of density in  $\gamma$ -form and  $\beta$ -form is

A. 0.9788

B. 1.02

C. 1.57

D. 0.6344

**Answer: A**



**Watch Video Solution**

**25.** The density of an ionic compounds ( $Mw = 58.5$ ) is  $2.165 \text{ kgm}^{-3}$  and the edge length of unit cell is 562 pm, then the closest distance between  $A^{\oplus} B^{\ominus}$  and  $Z_{eff}$  of unit cell is

A. 281 pm, 4

B. 562 pm, 2

C. 562 pm, 4

D. 281 pm, 2

**Answer: A**



**Watch Video Solution**

**26.** The edge length of unit cell of a metal ( $Mw = 24$ ) having cubic structure is  $4.53\text{\AA}$ . If the density of metal is  $1.74\text{gcm}^{-3}$ , the radius of metal is ( $N_A = 6 \times 10^{23}$ )



A. 180 pm

B. 160 pm

C. 140 pm

D. 190 pm

**Answer: B**



**Watch Video Solution**

27. The ratio of packing fraction in fcc, bcc, and cubic structure is, respectively,

A. 1 : 0.92 : 0.70

B. 0.70 : 0.92 : 1

C. 1 : 0.70 : 0.92

D. 0.92 : 0.70 : 1

**Answer: A**



**Watch Video Solution**

**28.** If  $R$  is the radius of the octahedral voids and  $r$  is the radius of the atom in close packing, then  $r / R$  is equal to

A. 2.41

B. 4.76

C. 3.22

D. 9.1

**Answer: A**



**Watch Video Solution**

**29.** How many unit cell are present in a cubic-shaped ideal crystal of  $NaCl$  of mass  $1.0g$ ?

A.  $1.28 \times 10^{21}$

B.  $1.71 \times 10^{21}$

C.  $2.57 \times 10^{21}$


D.  $5.14 \times 10^{21}$

**Answer: C**



**Watch Video Solution**

**30.** What type of crystal defect is indicated in the diagram given below



A. Both Frenkel and Schottky defects

B. Schottky defect

C. Interstitial defect

D. Frenkel defect

**Answer: B**



**Watch Video Solution**

**31.** The volume of atom present in a face-centred cubic unit cell of a metal ( $r$  is atomic radius ) is

A.  $\frac{20}{3}\pi r^3$

B.  $8\pi r^3$

C.  $4\pi r^3$

D.  $\frac{16}{3}\pi r^3$

**Answer: D**



**Watch Video Solution**

**32.** An elemental crystal has density of  $8570 \text{ kg m}^{-3}$ .

The packing efficiency is 0.67. If the closest distance between neighbouring atoms is  $2.86 \text{ \AA}$ . The mass of one atom is  $(1a\mu = 1.66 \times 10^{-27}) \text{ kg}$

A. 186 amu

B. 93 amu

C. 46.5 amu

D. 43 amu

**Answer: B**



**Watch Video Solution**

**33.** The atomic fraction ( $d$ ) of tin in bronze (fcc) with a density of  $7717\text{kgm}^{-3}$  and a lattice parameter of  $3.903\text{\AA}$  is

$(A_w\text{Cu} = 63.54, S_n = 118.7, 1a\mu = 1.66 \times 10^{-27}\text{kg})$

A. 0.01

B. 0.05

C. 0.10

D. 3.8

**Answer: B**



**Watch Video Solution**

**34.** Every atom or ion that forms an fcc unit cell is surrounded by

A. Six  $OV_s$  and eight  $TV_s$ .



B. Eight  $OV_s$  and Six  $TV_s$ .

C. Six  $OV_s$  and six  $TV_s$ .

D. Eight  $OV_s$  and four  $TV_s$ .

**Answer: A**



**Watch Video Solution**

**35.** How many  $Cs^+$  ions occupy the second nearest neighbour location of a  $Cs^+$  ion in the structure CsCl (8:8 coordination) ?

A. 8

B. 24

C. 6

D. 16

**Answer: C**



**Watch Video Solution**

**36.** A metal of density  $7.5 \times 10^3 \text{kgm}^{-3}$  has an fcc crystal structure with lattice parameter  $a = 400 \pm .$  Calculater the number of unit cells present in  $0.015\text{kg}$  of metal.

A.  $6.250 \times 10^{22}$

B.  $3.125 \times 10^{23}$

C.  $3.125 \times 10^{22}$

D.  $1.563 \times 10^{22}$

**Answer: C**



**Watch Video Solution**

**37.** The ratio of the volume of a tetragonal lattice unit cell to that of a hexagonal lattice unit cell is (both having same respective lengths)

A.  $\frac{\sqrt{3}}{2}abc$

B.  $\frac{2}{3\sqrt{3}}$

C.  $\frac{2}{\sqrt{3}\frac{a^2c}{b}}$

D. 1

**Answer: B**



**Watch Video Solution**

**38.** An fcc lattice has a lattice parameter  $a = 400$  pm. Calculate the molar volume of the lattice including all the empty space.

A.  $10.8mL$

B.  $96mL$

C.  $8.6mL$

D.  $9.6mL$

**Answer: D**



**Watch Video Solution**

**39.** A  $TV$  in fcc is formed by atoms at

A. 3 corners + 1 face centre

B. 3 face centres + 1 corner

C. 2 face centres + 2 corners

D. 2 face centres + 1 corner + 1 body centre

**Answer: B**



**Watch Video Solution**

**40.** A metal crystallizes in  $b$  lattice. The percent fraction of edge length not covered by atom is

A. 10.4 %

B. 13.4 %

C. 12.4 %

D. 11.4 %


**Answer: B**



**Watch Video Solution**

**41.** In the cubic lattice given below, the three distances between the atoms  $A - B$ ,  $A - C$ , and

$A - G$  are, respectively,



A.  $a, \sqrt{2}a, \sqrt{3}a$

B.  $a, \sqrt{3}a, \sqrt{2}a$

C.  $\frac{a}{2}, \frac{a}{\sqrt{2}}, \frac{\sqrt{3}a}{2}$


D.  $a, \frac{\sqrt{3}a}{2}, \sqrt{2}a$



Answer: A

 Watch Video Solution

42. In body-centred cubic lattice given below, the three distances  $AB$ ,  $AC$ , and  $\sqrt{3}$  are



A.  $a, \sqrt{2}a, \frac{\sqrt{3}a}{2}$

B.  $a, \frac{\sqrt{3}a}{2}, \sqrt{2}a$

C.  $\frac{\sqrt{3}a}{2}, \sqrt{2}a, a$

D.  $a, \frac{a}{\sqrt{2}}, \frac{\sqrt{3}a}{2}$

**Answer: A**



**Watch Video Solution**

**43.** Two ionic solids  $AB$  and  $CB$  crystallize in the same lattice. If  $r_{A^{\oplus}} / r_{B^{\ominus}}$  and  $r_{C^{\oplus}} / r_{B^{\ominus}}$  are 0.50 and 0.70, respectively, then the ratio of edge length of  $AB$  and  $CD$  is

A. 0.68

B. 0.78

C. 0.88

D. 0.98

**Answer: C**



**Watch Video Solution**

**44.** A molecule  $A_2B$  ( $Mw = 166.4$ ) occupies triclinic lattice with  $a = 5\text{\AA}$ ,  $b = 8\text{\AA}$ , and  $c = 4\text{\AA}$ . If the density of  $AB_2$  is  $5.2\text{gcm}^{-3}$ , the number of molecules present in one unit cell is

A. 2

B. 3

C. 4

D. 5

**Answer: B**



**Watch Video Solution**

**45.** Silicon dopped with group 13 and group 15 member element is, repectively, called ..... semiconductor

A.  $p$ -type,  $n$ -type

B.  $n$ -type,  $p$ -type

C.  $p$ -type

D.  $n$ -type

**Answer: A**



**Watch Video Solution**

**46.**  $Na$  and  $Mg$  crystallize in bcc- and fcc-type crystals, respectively, then the number of atoms of  $Na$  and  $Mg$  present in the unit cell of their respective crystal is

A. 4 and 2

B. 9 and 14

C. 14 and 9

D. 2 and 4

**Answer: B**



**Watch Video Solution**

**47.** The electrical conductivity of semiconductor is

A.  $10^8 \text{ ohm}^{-1} \text{ cm}^1$

B.  $10^{-22} \text{ ohm}^{-1} \text{ cm}^1$

C. In the range of  $10^{-9}$  to  $10^2 \text{ohm}^{-1} \text{cm}^{-1}$

D. None of the above

**Answer: C**



**Watch Video Solution**

**48.** Pure silicon and germanium are

A. Conductors

B. Insulators

C. Semiconductors

D. May be any one of the above

**Answer: B**



**Watch Video Solution**

**49.** A solid has a structure in which  $W$  atoms are located at the corners of a cubic lattice,  $O$  atom at the centre of edges, and  $Na$  atom at the centre of the cube. The formula for the compound is








**Answer: B**



**Watch Video Solution**

50. Which of the following is a ferroelectric compound?



D. None of these

**Answer: A**

 [Watch Video Solution](#)

51. The intermetallic compound  $LiAg$  crystallizes in cubic lattice in which both lithium and silver have coordination number of 8. The crystal class is

- A. Simple cubic
- B. Body-centred cubic
- C. Face-centred cubic
- D. None of these

**Answer: B**

 [Watch Video Solution](#)

52. The edge length of a face-centred cubic unit cell is  $508 \text{ \AA}$ . If the radius of the cation is  $110 \text{ \AA}$  the radius of the anion is

A.  $144 \text{ pm}$

B.  $288 \text{ pm}$

C.  $618 \text{ pm}$

D.  $398 \text{ pm}$

**Answer: A**



**Watch Video Solution**

53. In the crystals of which of the following ionic compounds would you expect maximum distance between the centres of the cations and anion?



**Answer: C**



**Watch Video Solution**

54. Schottky defect to crystals is observed when

A. Unequal number of cations and anions are missing from the lattice.

B. Equal number of cations and anions are missing from the lattice.

C. An ion leaves its normal site and occupies an interstitial site.

D. Density of the crystal is increased.

**Answer: B**



**Watch Video Solution**

55. How many kinds of space lattices are possible in a crystal?

A. 23

B. 7

C. 230

D. 14

**Answer: D**



**Watch Video Solution**

56. Potassium crystallizes with a

- A. Face-centred cubic lattice
- B. Body-centred cubic lattice
- C. Simple cubic lattice
- D. Orthorhombic lattice




**Answer: B**



**Watch Video Solution**

57. A compound formed by element  $A$  and  $B$  crystallizes in the cubic structure where  $B$  atoms

are atg the face-centres. The formula of the compound is



**Answer: A**



**Watch Video Solution**



58. The number of unit cells in 58.5g of  $NaCl$  is nearly

A.  $6 \times 10^{20}$

B.  $3 \times 10^{22}$

C.  $1.5 \times 10^{23}$

D.  $0.5 \times 10^{24}$

**Answer: C**



**Watch Video Solution**

59. The number of octahedral sites per sphere in fcc structure is

A. 8

B. 4

C. 2

D. 1

**Answer: D**



**Watch Video Solution**

60. The packing fraction for a body-centred cube is

A. 0.42

B. 0.53

C. 0.68

D. 0.82

**Answer: C**



**Watch Video Solution**

**61.** Which of the following has Frenkel defect?

A. Sodium chloride

B. Graphite

C. Silver bromide

D. Diamond

**Answer: C**



**Watch Video Solution**

**62.** In  $NaCl$ , the chloride ions occupy the space in a fashion of

A. fcc

B. bcc

C. Both

D. None

**Answer: A**



**Watch Video Solution**

**63.** To get  $n$ -type doped semiconductor, impurity to be added to silicon should have the following number of valence electrons

A. 2

B. 5

C. 3

D. 1

**Answer: B**



**Watch Video Solution**

**64.** The range of radius ratio (cationic to anionic) for an octahedral arrangement of ions in an ionic solid is

A.  $0.155 - 0.225$

B.  $0.225 - 0.414$

C.  $0.414 - 0.732$

D. 0.732 – 1.000

**Answer: C**



**Watch Video Solution**

65. When molten zinc is cooled to solid state, it assumes *hcp* structure. Then the number of nearest neighbours of zinc atom will be

A. 4

B. 6

C. 8

D. 12

**Answer: D**



**Watch Video Solution**

**66.** Superconductors are derived from the compounds of

A. *p*-block elements

B. Lanthanides

C. Actinides

D. Transition elements



**Answer: A**



**Watch Video Solution**

**67.** A semiconductor of  $Ge$  can be made  $p$ -type by adding

- A. Trivalent impurity
- B. Tetravalent impurity
- C. Pentavalent impurity
- D. Divalent impurity

**Answer: A**



Watch Video Solution

68. The interionic distance for cesium chloride crystal will be

A.  $a$

B.  $a/2$

C.  $\sqrt{3}a/2$



D.  $2a/\sqrt{3}$

**Answer: C**



Watch Video Solution

69. Which of the following metal oxides is anti-ferromagnetic in nature?




**Answer: A**



**Watch Video Solution**

70. What are types of following semiconductors *I* and *II*.



A.  $I \Rightarrow p - \text{type}, II \Rightarrow n - \text{type}$

B.  $I \Rightarrow n - \text{type}, II \Rightarrow p - \text{type}$

C. Both  $n$ -type

D. Both  $p$ -type

**Answer: B**

71. In the structure of diamond, carbon atoms appear at

A. 0, 0, 0, and  $\frac{1}{2}$ ,  $\frac{1}{2}$ ,  $\frac{1}{2}$





B.  $\frac{1}{4}$ ,  $\frac{1}{4}$ ,  $\frac{1}{4}$ , and  $\frac{1}{2}$ ,  $\frac{1}{2}$ ,  $\frac{1}{2}$

C. 0, 0, 0, and  $\frac{1}{4}$ ,  $\frac{1}{4}$ ,  $\frac{1}{4}$

D. 0, 0, 0, and  $\frac{3}{4}$ ,  $\frac{3}{4}$ ,  $\frac{3}{4}$

**Answer: A**

72. Which of the following figures represents the cross section of an *OV*?



**Answer: A**



Watch Video Solution

## Exercises Assertion Reasoning

1. Assertion (A) : in  $CsCl$  crystal,  $Cs^{\oplus}$  ions adopt bcc arrangement.

Reason (R) : For  $N$  atoms adopting bcc arrangement, there are  $2NTV_s$ .

A. If both (A) and (R) are correct, and (R) is the correct explanation of (A)

- B. If both ( $A$ ) and ( $R$ ) are correct, but ( $R$ ) is not the correct explanation of ( $A$ )
- C. If ( $A$ ) is correct, but ( $R$ ) is incorrect.
- D. If both ( $A$ ) is incorrect, but ( $R$ ) is correct.

**Answer: C**



**Watch Video Solution**

2. Assertion ( $A$ ) :  $CsCl$  crystal, the coordination number of  $Cs^{\oplus}$  ion is 8.

Reason ( $R$ ) :  $Cl^{\ominus}$  ion in  $CsCl$  adopt  $b$  type of packing,



- A. If both  $(A)$  and  $(R)$  are correct, and  $(R)$  is the correct explanation of  $(A)$
- B. If both  $(A)$  and  $(R)$  are correct, but  $(R)$  is not the correct explanation of  $(A)$
- C. If  $(A)$  is correct, but  $(R)$  is incorrect.
- D. If both  $(A)$  is incorrect, but  $(R)$  is correct.

**Answer: A**



**Watch Video Solution**

3. Assertion (A) : In sodium chloride crystal, the coordination number of  $Na^{\oplus}$  IS 6.

Reason (R ) : The sodium atom is smaller than chloring atom.

- A. If both (A) and (R) are correct, and (R) is the correct explanation of (A)
- B. If both (A) and (R) are correct, but (R) is not the correct explanation of (A)
- C. If (A) is correct, but (R) is incorrect.
- D. If both (A) is incorrect, but (R) is correct.

**Answer: B**



Watch Video Solution

4. Assertion (A) : The density of crystal having Schottky defect is lowered.

Reason (R) : The crystals suffering from Schottky defect have same number of cation and anions missing from their normal lattice sites.

A. If both (A) and (R) are correct, and (R) is

the correct explanation of (A)

B. If both (A) and (R) are correct, but (R) is

not the correct explanation of (A)

C. If ( $A$ ) is correct, but ( $R$ ) is incorrect.

D. If both ( $A$ ) is incorrect, but ( $R$ ) is correct.

**Answer: A**



**Watch Video Solution**

5. Assertion ( $A$ ) : In sodium chloride crystal,  $Na^{\oplus}$  ions occupy  $OVs$  while  $Cl^{\ominus}$  ions occupy vertices of octahedron.

Reason ( $R$ ) : The radius ratio of  $Na^{\oplus} : Cl^{\ominus}$  lies between 0.4 and 0.7.

- A. If both  $(A)$  and  $(R)$  are correct, and  $(R)$  is the correct explanation of  $(A)$
- B. If both  $(A)$  and  $(R)$  are correct, but  $(R)$  is not the correct explanation of  $(A)$
- C. If  $(A)$  is correct, but  $(R)$  is incorrect.
- D. If both  $(A)$  is incorrect, but  $(R)$  is correct.

**Answer: D**



**Watch Video Solution**

6. Assertion (A) : Solids containing  $F$  centres are paramagnetic.

Reason (R) : Solids containing  $F$  centres conduct electricity and it is  $n$ -type semiconduction.

- A. If both (A) and (R) are correct, and (R) is the correct explanation of (A)
- B. If both (A) and (R) are correct, but (R) is not the correct explanation of (A)
- C. If (A) is correct, but (R) is incorrect.
- D. If both (A) is incorrect, but (R) is correct.

**Answer: B**



Watch Video Solution

7. Assertion (A) : The electrical conductivity of a semiconductor increases with increase in temperature.

Reason (R) : With increase in temperature, large number of electrons from the valence band can jump to the conduction band.

A. If both (A) and (R) are correct, and (R) is the correct explanation of (A)

B. If both (A) and (R) are correct, but (R) is not the correct explanation of (A)

C. If ( $A$ ) is correct, but ( $R$ ) is incorrect.

D. If both ( $A$ ) is incorrect, but ( $R$ ) is correct.

**Answer: A**



**Watch Video Solution**

**8. Assertion (A) :** Group-13-doped crystals of  $Si$  are called  $p$ -type semiconductors.

**Reason (R ) :** Positive holes are responsible for the semiconducting properties.



- A. If both  $(A)$  and  $(R)$  are correct, and  $(R)$  is the correct explanation of  $(A)$
- B. If both  $(A)$  and  $(R)$  are correct, but  $(R)$  is not the correct explanation of  $(A)$
- C. If  $(A)$  is correct, but  $(R)$  is incorrect.
- D. If both  $(A)$  is incorrect, but  $(R)$  is correct.

**Answer: A**



**Watch Video Solution**

9. Assertion (A) : Group-15-doped crystal of  $Si$  are called  $n$ -type semiconductors.

Reason (R) : Neutrons are responsible for the semi-conducting properties.

- A. If both (A) and (R) are correct, and (R) is the correct explanation of (A)
- B. If both (A) and (R) are correct, but (R) is not the correct explanation of (A)
- C. If (A) is correct, but (R) is incorrect.
- D. If both (A) is incorrect, but (R) is correct.

**Answer: C**



Watch Video Solution

**10.** Assertion (A) : Non-stoichiometric compounds are called Bertholide compounds.  $NaCl$  and  $KCl$  crystal, when heated in an atmosphere of  $Na$  and  $K$  vapours, respectively, they impart violet and yellow colours to  $NaCl$  and  $KCl$ , respectively.

Reason (R ) : Metal excess defect is due to the presence of extra cations at the interstitial sites.

The excess metal ions move to the interstitial sites and the electrons to the neighbouring sites. The colour results by the excitation of these electrons by absorbing suitable energy from visible light.

When the excited electron comes back to the ground state, there is emission of radiation in the visible region and gives complimentary colour.

- A. If both ( $A$ ) and ( $R$ ) are correct, and ( $R$ ) is the correct explanation of ( $A$ )
- B. If both ( $A$ ) and ( $R$ ) are correct, but ( $R$ ) is not the correct explanation of ( $A$ )
- C. If ( $A$ ) is correct, but ( $R$ ) is incorrect.
- D. If both ( $A$ ) is incorrect, but ( $R$ ) is correct.

**Answer: D**



**Watch Video Solution**

11. Assertion (A) : Graphite is an example of tetragonal crystal system.

Reason (R) : For a tetragonal system,  $a = b \neq c$  and  $\alpha = \beta = 90^\circ, \gamma = 120^\circ$ .

- A. If both (A) and (R) are correct, and (R) is the correct explanation of (A)
- B. If both (A) and (R) are correct, but (R) is not the correct explanation of (A)
- C. If (A) is correct, but (R) is incorrect.
- D. If both (A) and (R) are incorrect.

**Answer: D**



**Watch Video Solution**

**12. Assertion (A) :** The size of a cation is larger in  $TV$  than in  $OV$ .

**Reason (R ) :** Cations occupy more space than anions in crystals packing.

A. If both (A) and (R) are correct, and (R) is the correct explanation of (A)

B. If both (A) and (R) are correct, but (R) is not the correct explanation of (A)

C. If ( $A$ ) is correct, but ( $R$ ) is incorrect.

D. If both ( $A$ ) and ( $R$ ) are incorrect.

**Answer: D**



**Watch Video Solution**

**13. Assertion (A) :** Antiferromagnetic substances on heating to high temperature become paramagnetic.

**Reason (R) :** On heating, the randomization of spins occurs.

- A. If both  $(A)$  and  $(R)$  are correct, and  $(R)$  is the correct explanation of  $(A)$
- B. If both  $(A)$  and  $(R)$  are correct, but  $(R)$  is not the correct explanation of  $(A)$
- C. If  $(A)$  is correct, but  $(R)$  is incorrect.
- D. If both  $(A)$  is incorrect but  $(R)$  is correct.

**Answer: A**



**Watch Video Solution**



14. Assertion (A) : Zinc blende and wurtzite both have  $f$  arrangement of  $S^{2-}$  ions.

Reason (R) : A unit cell of both has four formula units of  $ZnS$ .

- A. If both (A) and (R) are correct, and (R) is the correct explanation of (A)
- B. If both (A) and (R) are correct, but (R) is not the correct explanation of (A)
- C. If (A) is correct, but (R) is incorrect.
- D. If both (A) and (R) are incorrect.

**Answer: D**



Watch Video Solution

15. Assertion (A) : Covalent crystals have higher melting point.

Reason (R) : Covalent bonds are stronger than ionic bonds.

A. If both (A) and (R) are correct, and (R) is the correct explanation of (A)

B. If both (A) and (R) are correct, but (R) is not the correct explanation of (A)

C. If (A) is correct, but (R) is incorrect.

D. If both (*A*) is incorrect but (*R*) is correct.

**Answer: C**



**Watch Video Solution**

**16.** Assertion (*A*) : *hcp* is more closely packed than *p*.

Reason (*R*) : *hcp* has a *CN* of 12, whereas *p* has a *CN* of 8.

A. If both (*A*) and (*R*) are correct, and (*R*) is the correct explanation of (*A*)

- B. If both ( $A$ ) and ( $R$ ) are correct, but ( $R$ ) is not the correct explanation of ( $A$ )
- C. If ( $A$ ) is correct, but ( $R$ ) is incorrect.
- D. If both ( $A$ ) is incorrect but ( $R$ ) is correct.

**Answer:**



**Watch Video Solution**

**17. Assertion (A) :** Frenkel defects are shown by  $AgX$

.

**Reason (R) :**  $Ag^{\oplus}$  ions have small size.

- A. If both  $(A)$  and  $(R)$  are correct, and  $(R)$  is the correct explanation of  $(A)$
- B. If both  $(A)$  and  $(R)$  are correct, but  $(R)$  is not the correct explanation of  $(A)$
- C. If  $(A)$  is correct, but  $(R)$  is incorrect.
- D. If both  $(A)$  is incorrect but  $(R)$  is correct.

**Answer: A**



**Watch Video Solution**

18. Assertion (A) : Triclinic system is the most unsymmetrical system.

Reason (R) : No axial angle is equal to  $90^\circ$  in triclinic system.

- A. If both (A) and (R) are correct, and (R) is the correct explanation of (A)
- B. If both (A) and (R) are correct, but (R) is not the correct explanation of (A)
- C. If (A) is correct, but (R) is incorrect.
- D. If both (A) is incorrect but (R) is correct.

**Answer: B**



Watch Video Solution

19. Assertion (A) : In the rock salt type structure, all the  $OV_s$  are occupied by  $Na^{\oplus}$  ions.

Reason (R) : Number of  $OV_s =$  Number of  $Cl^{\ominus}$  ions in the packing.

- A. If both (A) and (R) are correct, and (R) is the correct explanation of (A)
- B. If both (A) and (R) are correct, but (R) is not the correct explanation of (A)
- C. If (A) is correct, but (R) is incorrect.

D. If both ( $A$ ) is incorrect but ( $R$ ) is correct.

**Answer: B**



**Watch Video Solution**

## Exercises Interger

1. If a solid  $A^{\oplus}B^{\ominus}$  having  $ZnS$  Structure is heated so that the ions along two of the axis passing through the face centre particles are lost and bivalent ion ( $Z$ ) enters herre to maintain the



electrical neutrality, so that the new formula unit becomes  $A_xB_yC_c$ , report the value of  $x + y + c$ .

 [Watch Video Solution](#)

2. Metal  $M$  of radius  $50nm$  is crystallized in  $f$  type and made cubical crystal such that face of unit cells aligned with face of cubical crystal. If the total number of metal atoms of  $M$  at all faces of cubical crystal is  $6 \times 10^{30}$ , then the area of one face of cubical crystal is  $A \times 10^{16}m^2$ . Find the value of  $A$ .

 [Watch Video Solution](#)

3.  $O_{2-}$  ions are arranged in p in spinel structure.

$A^{2+}$  ions occupy  $1/8$  of  $TV_s$  and  $B^{\oplus}$  ions occupy

half of  $OV$ . The void volume of unit cell =  $0.11\text{\AA}$ .

Find the value of  $A$  ?



[View Text Solution](#)

4. Find the coordination of  $Na^{\oplus}$  in  $Na_2O$ .



[Watch Video Solution](#)

5. A bcc lattice is made up of hollow spheres of  $B$ .

Spheres of solids  $A$  are present in hollow spheres


of  $B$ . The radius of  $A$  is half of the radius of  $B$ . The ratio of total volume of spheres of  $B$  unoccupied by  $A$  in a unit cell and volume of unit cell is  $A \times \frac{\pi\sqrt{3}}{64}$ .

Find the value of  $A$ .



[Watch Video Solution](#)

6. In the figure given below, four parallelograms are shown. How many parallelograms are a unit cells?




 [Watch Video Solution](#)

7. Cesium atoms are the largest naturally occurring atoms. The radius of  $Cs$  atom is  $2.6\text{\AA}$ . The number of moles of  $Cs$  atoms to be laid side by side to give a row of  $Cs$  atoms  $2.5\text{cm}$  long is  $x \times 10^{-17}$ . Find the value of  $x$ .

8. The following figure shows the unit cell of a compound, i.e., a mixed oxide of yttrium, barium, and copper. The formula of mixed oxide is  $Y_aBa_bCu_cO_d$ .

Find the value of  $(a + b + c + d)$ .



9. A solid has a structure in which  $X$  atoms are located at cubic corners of unit cell,  $O$  atoms are at the edge centres and  $Y$  atoms at cube centre.

Then the formula of compound is  $X_a Y_b O_c$

If two atoms of  $O$  missing from any of two edge centres per unit cell, then the molecular formula is

$X_a Y_b O_z$ . Then, find the value of

$$(x + y + z) - (a + b + c).$$



[Watch Video Solution](#)

Exercises Fill In The Blanks

1. Although amorphous solids do not possess the long range order of crystals, they do have ..... just as liquids do.



**Watch Video Solution**

2. When a piezoelectric crystal is deformed by mechanical stress ..... is produced due to the displacement of ions.



**Watch Video Solution**

3. Unlike paramagnetic substance, ferromagnetic substances show ..... even if the external magnetic field is removed.



[Watch Video Solution](#)

4. The number of atoms touching a particular atom in a crystal is called its .....



[Watch Video Solution](#)



5. The number of atoms present per unit cell in simple, fcc and bcc are ....., ....., and ....., respectively.

 [Watch Video Solution](#)

6. The  $ABCABC$  type packing is called .....

 [Watch Video Solution](#)

7. The compounds having the general molecular formula  $A^{2+}Fe_{2.04}$  are called .....





Watch Video Solution

8. If  $r_{\oplus} / r_{\ominus}$  for a crystal is 0.50, it has ..... structure.



Watch Video Solution

9. Introducing a defect in a crystal by adding impurity is called ..... .



Watch Video Solution

10. When a substance conducts electricity without any resistance, it is called a .....

 [Watch Video Solution](#)

11. A liquid which is permanently supercooled is frequently called a .....

 [Watch Video Solution](#)

12. In NaCl ionic crystal, each  $Na^+$  ion is surrounded by \_\_\_\_\_  $Cl^-$  ions and each  $Cl^-$

ion is surrounded by \_\_\_\_\_  $Na^+$  ions.



[Watch Video Solution](#)

**13.** For  $N$  atoms in a crystal with  $N_i$  interstitial position in its structure. If there are  $n$  Frenkel defects in the crystal, then  $n = \dots\dots$ .



[Watch Video Solution](#)

**14.** If a crystal contains a total of  $N$  atoms and  $n$  Schottky defects are produced by removing  $n$

cations and  $r$  anions from the interior of the crystal,

then  $n = \dots\dots$  .



Watch Video Solution

15. The distance between any two  $TV_s$  formed one any body diagonal of a closest packed structure is  $= x \times a$ , where  $a$  is the edge length of closest packed structure.

the value of  $x = \dots\dots\dots$  .



Watch Video Solution

1. It is much more difficult to describe the crystal structure of compounds than those of elements.



[Watch Video Solution](#)

2. If the radius of the spheres in the close packing is  $R$  and the radius of octahedral voids is  $r$ , then  $r = 0.414R$ .



[Watch Video Solution](#)

3. In crystals, the state of complete order and of lowest energy is formed at  $0^{\circ}C$ .



[Watch Video Solution](#)

4. STATEMENT -1 : Amorphous solids are isotropic

STATEMENT -2 : Amorphous solids lack a regular three-dimensional arrangement of atoms.



[Watch Video Solution](#)

5. In bcc lattice, the atoms at the corners of the unit cell are in contact with each other.



Watch Video Solution

6. The cubic close-packed structure is based on an fcc unit cell.



Watch Video Solution

7. In  $ZnS$  (zinc blende) structure, the  $CN$  of each ion is 4.







Watch Video Solution

8. Solids with Schottky defects are electrical insulators.



Watch Video Solution

9. Platinum crystallizes in fcc crystal with a unit cell length  $a$ . The atomic radius of platinum is therefore  $a\sqrt{2}/2$ .



Watch Video Solution

10. There are four formula units in fluorite and antiferite structure.

 [Watch Video Solution](#)

11. In antiferite structure, 50% of  $TV_s$  are occupied by anion.

 [Watch Video Solution](#)

12. In fluorite structure, 100% of  $TV_s$  are occupied by cations.





Watch Video Solution

13. In diamond,  $CN$  of carbon is 4 and its unit cell has 8 carbon atoms.



Watch Video Solution

14.  $ZnS$  exists in two different form: zinc blende and wurtzite. Both occur in 4:4 coordination compounds. Zinc blende has an fcc structure and wurtzite has an hcp structure.



Watch Video Solution

15.  $Fe^{III}(Fe^{II}Fe^{III})O_4$  represent an inverse 2:3 spinel structure.



Watch Video Solution

16. The addition of  $CaCl_2$  to a  $KCl$  crystal lowers the density of the  $KCl$  crystal.



Watch Video Solution

17. The maximum number of Bravais lattices is shown by tetragonal-type crystals.



 [Watch Video Solution](#)

18. Bragg reflection can occur only when  $\gamma \leq 2d$ .

 [Watch Video Solution](#)

19.  $TVs$  and  $OVs$  both are found in hcp and simple cube.

 [Watch Video Solution](#)

[Exercises Archives Linked Comprehension](#)

1. In a hexagonal system system of crystals, a frequently encountered arrangement of atoms is described as a hexagonal prism. Here, the top and bottom of the cell are regular hexagons, and three atoms are sandwiched in between them. A space-filling model of this structure, called hexagonal close-packed is constituted of a sphere on a flat surface surrounded in the same plane by six identical spheres as closely as possible. Three spheres are then placed over the first layer so that they touch each other and represent the second layer so that they touch each other and present the second layer. Each one of the three spheres touches three spheres of the bottom layer. Finally, the

second layer is covered with a third layer identical to the bottom layer in relative position. Assume the radius of every sphere to be  $r$ .

The number of atom in this hcp unit cell is

- A. 4
- B. 6
- C. 12
- D. 17

**Answer: B**



[Watch Video Solution](#)

2. In a hexagonal system of crystals, a frequently encountered arrangement of atoms is described as a hexagonal prism. Here, the top and bottom of the cell are regular hexagons, and three atoms are sandwiched in between them. A space-filling model of this structure, called hexagonal close-packed is constituted of a sphere on a flat surface surrounded in the same plane by six identical spheres as closely as possible. Three spheres are then placed over the first layer so that they touch each other and represent the second layer so that they touch each other and present the second layer. Each one of the three spheres touches three spheres of the bottom layer. Finally, the



second layer is covered with a third layer identical to the bottom layer in relative position. Assume the radius of every sphere to be  $r$ .

The volume of this hcp unit cell is

A.  $24\sqrt{2}r^3$

B.  $16\sqrt{2}r^3$

C.  $12\sqrt{2}r^3$

D.  $\frac{64}{3\sqrt{3}r^3}$

**Answer: A**



**Watch Video Solution**

3. In a hexagonal system of crystals, a frequently encountered arrangement of atoms is described as a hexagonal prism. Here, the top and bottom of the cell are regular hexagons, and three atoms are sandwiched in between them. A space-filling model of this structure, called hexagonal close-packed is constituted of a sphere on a flat surface surrounded in the same plane by six identical spheres as closely as possible. Three spheres are then placed over the first layer so that they touch each other and represent the second layer so that they touch each other and present the second layer. Each one of the three spheres touches three spheres of the bottom layer. Finally, the

second layer is covered with a third layer identical to the bottom layer in relative position. Assume the radius of every sphere to be  $r$ .

The empty space in this hcp unit cell is

- A. 74 %
- B. 48.6 %
- C. 32 %
- D. 26 %

**Answer: D**



**Watch Video Solution**

1. Which of the following statements is/are correct?

A. The coordination number of each type of ion

in  $CsCl$  crystal is 8.

B. A metal that crystallizes in  $b$  structure has a

coordination number of 12.

C. A unit cell of an ionic crystal shares some of

its ions with other unit cells.

D. The length of the unit cell in  $NaCl$  is 552 pm (

$r_{Na^{\oplus}} = 95 \text{ pm}, r_{Cl^{\oplus}} = 181 \pm$  ).

**Answer: A::C::D**



**Watch Video Solution**

2. Which of the following statement regarding defects in solids is/are correct?

A. Frenkel defect is usually favoured by a very small difference in the sizes of cation and anion.

B. Frenkel defect is a dislocation defect.

C. Trapping of an electron in the lattice leads to the formation of  $F^-$ -centre.

D. Schottky defects have no effect on the physical properties of solids.

**Answer: B::C**

 [Watch Video Solution](#)

**Exercises Archives Single Correct**

1.  $CsBr$  has  $b$  structure with edge length of  $43 \pm$  .

The shortest interionic distance between cation and

anion is

A. 37.2

B. 18.6

C. 74.4

D. 43

**Answer: A**



**Watch Video Solution**

2. The coordination number of a metal crystallizing in a hexagonal close-packed structure is

A. 12

B. 4

C. 8

D. 6

**Answer: A**







**Watch Video Solution**

3. In a solid AB having  $NaCl$  structure 'A' atoms occupy the corners & face centre of the cubic unit cell. If all the face centered atoms along one of the



axes are removed, then the resultant stoichiometry of the solid is





**Answer: D**



**Watch Video Solution**

4. A substance  $A_xB_y$  crystallizes in a face-centred cubic lattice in which atoms  $A$  occupy the centres of each face of the cube. Identify the correct composition of the substance  $A_xB_y$ .



D. Cannot be specified

**Answer: A**



**Watch Video Solution**

5. In which of the following crystals, alternate tetrahedral voids are occupied?




**Answer: B**



**Watch Video Solution**

6. The packing efficiency of a two-dimensional square unit cell shown below is



A. 39.27 %

B. 68.02 %

C. 74.05 %

D. 78.54 %


**Answer: D**



**Watch Video Solution**

7. A compound  $M_pX_q$  has cubic close packing (p) arrangement of  $X$ . Its unit cell structure is shown

below. The empirical formula of the compound is



a.  $MX$

b.  $MX_2$

c.  $M_2X$

A.  $MX$

B.  $MX_2$

C.  $M_2X$

D.  $M_5X_{14}$

**Answer: B**



**Watch Video Solution**

8. Experimentally it was found that a metal oxide has formula  $M_{0.98}O$ , Metal  $M$ , is present as  $M_{+2}$  and  $M_{+3}$  in its oxid. Fraction of the metal which exist as  $M_{(+3)}$  would be :

A. 4.08 %

B. 6.05 %

C. 5.08 %


D. 7.01 %

Answer: A

 Watch Video Solution

9. The arrangement of  $X^\ominus$  ions around  $A^\oplus$  ion in solid  $AX$  is given in the figure (not drawn to scale).

If the radius of  $X^\ominus$  is  $250 \text{ \AA}$ , the radius of  $A^\oplus$  is





A.  $104 \pm$

B.  $125 \pm$

C.  $183 \pm$

D.  $57 \pm$

**Answer: A**



**Watch Video Solution**

10.  $CsCl$  crystallizes in body centred cubic lattice. If ' $a$ ' us its edge length then which of the following expressions is correct ?

$$\text{A. } r_{Cs^{\oplus}} + r_{Cl^{\ominus}} = \frac{\sqrt{3}}{2}a$$

$$\text{B. } r_{Cs^{\oplus}} + r_{Cl^{\ominus}} = \sqrt{3}$$

$$\text{C. } r_{Cs^{\oplus}} + r_{Cl^{\ominus}} = 3a$$

$$\text{D. } r_{Cs^{\oplus}} + r_{Cl^{\ominus}} = \frac{3a}{2}$$

**Answer: A**



**Watch Video Solution**

**Exercises Archives Assertion Reasoning**

1. Statement I: In any ionic solid  $[MX]$  with Schottky defect, the number of positive and negative ions are

same.

Statement II: An equal number of cation and anion vacancies is present.

- A. Statement I is true, Statement II is true, Statement II is a correct explanation of Statement I.
- B. Statement I is true, Statement II is true, Statement II is not a correct explanation of Statement I.
- C. Statement I is true, Statement II is false.
- D. Statement I is false, Statement II is true.

**Answer: A**



**Watch Video Solution**

## Exercises Archives Interger

1. Find the number of hexagonal faces that are present in a truncated octahedral.



**Watch Video Solution**

## Exercises Archives Subjective

1. Sodium metal crystallises in body centred cubic lattice with cell edge  $4.29\text{\AA}$ . What is the radius of sodium atom?



[Watch Video Solution](#)

2. A metallic crystal crystallizes into a lattice containing a sequence of layers  $ABABAB\dots$ . Any packing of spheres leaves out voids in the lattice. What percentage by volume of this lattice is empty space?



[Watch Video Solution](#)

3. Chromium metal crystallizes with a body-centred cubic lattice. The length of the unit cell edge is found to be 287pm. Calculate the atomic radius. What would be the density of chromium in  $gcm^{-3}$ ?




[Watch Video Solution](#)

4. A metal crystallizes into two cubic phases, face-centred cubic and body-centred cubic, which have unit cell lengths 3.5 and 3.0Å, respectively. Calculate the ration of densities of fcc and bcc.



[Watch Video Solution](#)

5. The figure below show the locations of atoms in three crystallographic planes in an fcc lattice. Draw the unit cells for these structure and identify these planes in your diagrams.



[Watch Video Solution](#)

6. You are given marbles of diameter  $10\text{mm}$ . They are to be placed such that their centres are lying in a square bound by four lines each of length  $40\text{mm}$ . What will be the arrangements of marbles in a plane so that maximum number of marbles can be placed inside the area? Sketch the diagram and derive expression for the number of molecules per unit area.



[Watch Video Solution](#)



7. The crystal  $AB$  (rock salt structure) has molecular weight  $6.023Yu$ , where  $Y$  is an arbitrary number in  $u$ . If the minimum distance between cation and anion is  $\frac{Y^1}{3}nm$  and the observed density is  $20kgm^{-3}$ . Find

a. The density in  $kgm^{-3}$ . and

b. The type of defect



**Watch Video Solution**

8. An element crystallises in  $f.c.c.$  lattice having edge length  $400pm$ . Calculate the maximum

diameter, which can be placed in interstitial sites without disturbing the structure.

 [Watch Video Solution](#)

9. The edge length of unit cell of a metal having molecular weight  $75 \text{ g mol}^{-1}$  is  $5 \text{ \AA}$  which crystallizes in cubic lattice. If the density is  $2 \text{ g cm}^{-3}$ , then find the radius of metal atom ( $N_A = 6 \times 10^{23}$ ). Give the answer in pm.

 [Watch Video Solution](#)

1. A compound formed by elements X and Y crystallizes in the cubic structure where Y atoms are at the corners of the cube and X atoms are at the alternate faces. What is the formula of the compound. ?



[Watch Video Solution](#)

2. Calculate the number of atoms in a cubic unit cell having one atom on each corner and two atoms one each diagonal.



[Watch Video Solution](#)

3. A compound made up of elements  $A$  and  $B$  crystallizes in the cubic structures. Atoms  $A$  are present on the corners as well as face centres whereas atoms  $B$  are present on the edge centres as well as body centre. What is the formula of the compound? Draw the structure of its unit cell.



[Watch Video Solution](#)

4. In the fcc arrangement of  $A$  and  $B$  atoms whose  $A$  atoms are at corners of the unit cell and  $B$  are at

the face centres one of the  $A$  atom is missing from one corner in each unit cell. What is the simplest formula of the compound?



[Watch Video Solution](#)

5. A solid  $AB$  has  $NaCl$  structure. If the radius of the cation  $A$  is 100 pm, what is the radius of anion  $B$ ?



[Watch Video Solution](#)

6. In a crystallizes solid, anions  $B$  are arranged in cubic close packing, cations  $A$  are equally distributed between octahedral and tetrahedral voids, what is the formula of the solid?



[Watch Video Solution](#)

7. In sapphire, oxide ions are arranged in hexagonal close packing and aluminium ions occupy two-thirds of the octahedral voids. What is the formula of sapphire?



[Watch Video Solution](#)

8. The density of  $NH_4Cl$  is  $1.534\text{gcm}^{-3}$ . It crystallizes in the  $CsCl$  lattice.

a. Calculate the length of the length of the edge of  $NH_4Cl$  unit cell.

b. Calculate the shortest distance between a  $NH_4^{\oplus}$  ion and a  $Cl^{\ominus}$  ion.

c. Calculate the radius of  $NH_4^{\oplus}$  ion if the radius of the  $Cl^{\ominus}$  ion is 181 pm



[Watch Video Solution](#)

9. A solid  $A^{\oplus}B^{\ominus}$  has  $NaCl$ -type close-packed structure. If the radius of the cation is 90 pm,

calculate the probable range of the radius of the anion.



[Watch Video Solution](#)

10. A solid  $A^+B^-$  has *NaCl*-type close-packed structure. If the anion has a radius of 250 pm, what should be the ideal radius for the cation? Can a cation  $C^+$  having radius of 180 pm be slipped into the tetrahedral site of the crystal  $A^+B^-$ ? Give reason for your answer.



[Watch Video Solution](#)



11. In a close-packed structure of oxides, one-eighth of the tetrahedral holes is occupied by bivalent cations ( $A$ ) and half of the octahedral hole are occupied by trivalent cations ( $B$ ), calculate the molecular formula of the oxide.



Watch Video Solution

12. a.  $MgO$  has the structure of  $NaCl$  and  $TlCl$  has the structure of  $CsCl$ . What are the coordination number of the ions in  $MgO$  and  $TlCl$ ?

If the closed-packed cations in an  $XY$ -type solid

have a radius of 73.2 pm, what would be the maximum and minimum sizes of the anions filling voids?

c.  $Fe_2O_3$  (haematite) forms ccp arrangement of  $O^{2-}$  ions with  $Fe_{3+}$  ions occupying interstitial positions. Predict whether  $Fe^{3+}$  ions are in the  $OV$  or  $TV$ . Given  $r_{Fe^{3+}} = 0.7\text{\AA}$  and  $r_{O^{2-}} = 1.4\text{\AA}$

d. A solid  $XY$  has  $CsCl$ -type structure. The edge length of the unit cell is  $400 \pm$  Calculate the distance of closest approach between  $X^{\oplus}$  and  $Y^{\ominus}$  ions.



Watch Video Solution

## Ex 1 1 Objective

1. Which of following statements is correct in the zinc-blende-type structure of an ionic compound?

A. Coordination number of each cation and anion is 2.

B. Coordination number of each cation and anion is 4.

C. Coordination number of each cation and anion is 6.

D. Coordination number of each cation and anion is 8.

**Answer: B**



**Watch Video Solution**

2. In a body-centred cubic unit cell of closest packed atoms, the radius of atom in terms of atom is terms of edge length  $a$  of the unit cells is

A.  $a/2$

B.  $a/\sqrt{2}$

C.  $a / 2\sqrt{2}$

D.  $\sqrt{3}a / 4$

**Answer: D**



**Watch Video Solution**

3. Which of the following expressions is correct in the case of a sodium chloride unit cell (edge length,  $a$ )?

A.  $r_{\oplus} + r_{\ominus} = a$

B.  $r_{\oplus} + r_{\ominus} = a/2$

$$C. r_{\oplus} + r_{\ominus} = 2a$$

$$D. r_{\oplus} + r_{\ominus} = \sqrt{2}a$$

**Answer: B**



**Watch Video Solution**

4. In silicon crystal,  $Si$  atoms form fcc arrangement where 4 out of 8  $TVs$  are also occupied by  $Si$  atoms.

$Z_{eff}$  of unit cell is

A. 1

B. 2

C. 4

D. 8

**Answer: D**



**Watch Video Solution**

5. Which of the following crystal systems exist in  $bc$ , end-centred,  $fc$ , as well as primitive unit cell?

A. Hexagonal

B. Cubic

C. Triclinic


D. Orthorhombic

**Answer: D**



**Watch Video Solution**

6. In a cubic,  $A$  atoms are present on alternative corners,  $B$  atoms are present on alternate faces, and  $C$  atoms are present on alternate edges and body centred of the cube. The simplest formula of the compound is





C.  $ABC_4$

D.  $ABC_2$

**Answer: B**



**Watch Video Solution**

7. The fraction of octahedral voids filled by  $Al^{3+}$  ion in  $Al_2O_3$  ( $r_{Al^{3+}} / r_{O^{2-}} = 0.43$ ) is

A. 0.43

B. 0.287

C. 0.667

D. 1

**Answer: C**



**Watch Video Solution**

**8.** In the closest packing atoms, there are

A. One tetrahedral voids and two octahedral voids per atom

B. Two tetrahedral voids and one octahedral void per atom

C. Two of each tetrahedral and octahedral voids  
per atom

D. One of the each tetrahedral and octahedral  
void per atom

**Answer: B**



**Watch Video Solution**

9. Which of the following statement si correct for the body-centred cubic structture of an ionic compound?

A. Coordination number of each cation and anion is 2.

B. Coordination number of each cation and anion is 4.

C. Coordination number of each cation and anion is 6.

D. Coordination number of each cation and anion is 8.

**Answer: D**



**Watch Video Solution**

10. Aluminium metal has a density of  $2.72\text{gcm}^{-3}$  and crystallizes in a cubic lattice with an edge of  $404 \pm$  . Which of the following is correct?

A. It forms bcc unit cell

B. It forms fcc unit cell

C. Its  $CN = 8$





D. Its  $CN$  is 6

**Answer: B**



**Watch Video Solution**

11. If atoms are removed from half of the edge-centred  $OV_s$  in  $RbBr$ , then the molecular formula of unit cell is



**Answer: C**



**Watch Video Solution**

12.  $ThO_2$  exists in fluorite structure, what is the effective number of bivalent ion in the unit cell of  $ThO_2$ ?

A. 2

B. 4

C. 1

D. 8

**Answer: D**



**Watch Video Solution**

13. What is the coordination number of  $Th^{4+}$  in  $ThO_2$ ?

A. 4

B. 8

C. 6

D. 12

**Answer: C**



**Watch Video Solution**



14. The coordination number  $Cs$  and  $Br$  in  $CsBr$  are, respectively,

A. 8, 8

B. 6, 6

C. 8, 6

D. 6, 8

**Answer: A**



**Watch Video Solution**

15. The fraction of total volume occupied by atoms in a simple cube is

A.  $\sqrt{3}\pi / 8$

B.  $\pi / 6$

C.  $\pi / 3$

D.  $\sqrt{2}\pi / 3$

**Answer: B**



**Watch Video Solution**

16. Xenon crystallises in face - centered cubic , and the edge of the unit cell is 620 pm .The radius of a xenon atom is

A. 219.20 pm

B. 438.5 pm

C. 290.3 pm

D. 318.53 pm

**Answer: A**



**Watch Video Solution**

17. In  $BeO$  (zinc blende structure),  $Mg^{2+}$  is introduced in available  $TV$  is. The coordination numbers of  $Be^{2+}$  and  $Mg^{2+}$  are, respectively,

A. 8, 8

B. 6, 6

C. 4, 4



D. 8, 6

**Answer: C**



**Watch Video Solution**

18. If the ions are removed from a single body diagonal in above case after doping, then the molecular formula of the unit cell would be







**Answer: B**



**Watch Video Solution**

19. In spinel,  $Mg^{2+}$  is present in one-eighth of  $TVs$  in an fcc lattice of oxide ions and  $Al^{3+}$  ions are present in half of the  $OVs$ . The Formula of spinel is



**Answer: C**



**Watch Video Solution**

## Ex 1 2 Subjective

1. The number of Schottky defects ( $n$ ) present in an ionic compound containing  $N$  ions at temperature  $T$  is given by  $n = Ne^{-E/2KT}$ , where  $E$  is the energy required to create  $n$  Schottky defects and  $K$  is the Boltzmann constant, If the mole fraction of Schottky defect in  $NaCl$  crystal at  $2900K$  is  $X$ , then calculate  $-\ln(x)$ ,

Given:  $\Delta H$  of Schottky defect =  $2eV$  and

$$K = 1.38 \times 10^{-23} JK^{-1}$$

$$1eV = 1.608 \times 10^{-19} J$$



Watch Video Solution

2.  $FeO$  crystallizes in  $NaCl$ -type of crystal lattice.

The crystals of  $FeO$  are deficient in iron and are always non-stoichiometric. Some cationic sites are vacant and some contain  $Fe^{3+}$  ions but the combination is such that the structure is electrically neutral. The formula approximates to  $Fe_{0.95}O$ .

- What is the ratio of  $Fe^{2+}$  to  $Fe^{3+}$  ions in the solid?
- What percentage of cation sites are vacant?




[Watch Video Solution](#)



1. The structure shown here represents

3. The structure shown here represents



a. Schottky defect

b. Frenkel defect

A. Schottky defect

B. Frenkel defect

C. Metal excess defect


D. None

**Answer: A**



**Watch Video Solution**

2. The structure shown here represents



A. Schottky defect

B. Frenkel defect

C. Metal excess defect because of absent anion

D. Metal excess defect because of excess cation

**Answer: B**



**Watch Video Solution**

3. In  $AgCl$ , the  $Ag^{\oplus}$  ions are displaced from their lattice position to an interstitial position. Such a defect is called

A. Schottky defect

B. Frenkel defect

C. Wadsley defect

D. Colour centre

**Answer: B**



**Watch Video Solution**

4.  $NaCl$  shows Schottky defects and  $AgCl$  shows Frenkel defects. Their electrical conductivity is due to the

A. Motion of electrons and not the motion of ions

B. Motion of ions and not the motion of electrons

C. Lower coordination number of  $NaCl$

D. Higher coordination number of  $AgCl$

**Answer: B**



**Watch Video Solution**

5. Amorphous solids are classified as

A. Isotropic and supercooled liquids

B. Anisotropic and supercooled liquids

C. Isoenthalpic and supercooled liquids

D. Isotropic and supercooled solids

**Answer: A**



**Watch Video Solution**

**6. Due of Frenkel defect**

- A. Density of the crystal increases
- B. Conduction and increases
- C. Conduction decreases
- D. Crystal becomes charged electrically

**Answer: B**



**Watch Video Solution**

7. Which of the following statement is//are correct?

A. All ferroelectric solids are piezoelectric.

B. All piezoelectric solids are ferroelectric.

C. Lead zirconate ( $PbZrO_3$ ) is a an antiferroelectric is an antiferroelectric crystal.

D.  $BaTiO_3$ , (barium titanate) is a ferroelectric crystal.

**Answer: A::C::D**



**Watch Video Solution**



8. Which of the following statement is//are correct?

A. A diode is a combination of  $p$ - and  $n$ -type semiconductors which is used as a rectifier.

B. Transistors are sandwich semiconductors of the type  $pn$  or  $npn$  which are used to detect or amplify radio or audio signals.

C. Monoxides of transition metals, all of which possess  $NaCl$  structures, show very large variations in electrical properties.

D.  $ReO_3$  has the conductivity as well as appearance like that of copper.

**Answer: A::B::C::D**



**Watch Video Solution**

9. Which of the following statement is//are correct?

A. Piezoelectric crystals are used as pick-ups in record players, they are also used in microphones, ultrasonic generators, and sonar detectors.

B.  $BaTiO_3$ , Rochelle salt,  $KH_2PO_4$ , and quartz are ferroelectric and piezoelectric solids.

C. The temperature above which no ferromagnetism is observed is called Curie temperature.

D. The temperature at which the material shows super-conductivity is called transition temperature.

**Answer: A::B::C::D**



**Watch Video Solution**

